# **Journal of The Korean Wood Science and Technology**

Vol. 44 No. 6

November 2016

# CONTENTS-I

Predicting Lamina Yield from Logs of Different Diameters for Cross Laminated Timber Production Gi Young Jeong, Jun-Jae Lee, Hwanmyeong Yeo, So Sun Lee
Energy Efficiency of Fluidized Bed Drying for Wood Particles Yonggun Park, Yoon-Seong Chang, Jun-Ho Park, Sang-Yun Yang, Hyunwoo Chung, Soo-Kyeong Jang, In-Gyu Choi, Hwanmyeong Yeo
Analysis on Wood Quality, Geometry Factor, and Their Effects on Lathe Check of Samama ( <i>Anthocephalus macrophyllus</i> ) Veneer Tekat Dwi Cahyono, Imam Wahyudi, Trisna Priadi, Fauzi Febrianto, Effendi Tri Bahtiar, Eka Novriyanti
Effect of Phenol Formaldehyde Impregnation on The Physical and Mechanical Properties of Soft-Inner Part of Oil Palm Trunk Rudi Hartono, Wahyu Hidayat, Imam Wahyudi, Fauzi Febrianto, Wahyu Dwianto, Jae-Hyuk Jang, Nam-Hun Kim
Study on Rapid Measurement of Wood Powder Concentration of Wood-Plastic Composites using FT-NIR and FT-IR Spectroscopy Techniques Byoung-kwan Cho, Santosh Lohoumi, Chul Choi, Seong-min Yang, Seog-goo Kang
Comparative Analysis of Gross Calorific Value by Determination Method of Lignocellulosic Biomass Using a Bomb Calorimeter Young Min Ju, Byung-Jun Ahn, Jaejung Lee

K5W5T The Korean Society of Wood Science & Technology



# Journal of The Korean Wood Science and Technology

### Aims and Scope

The *Journal of The Korean Wood Science and Technology (JKWST)* launched in 1973 as an official publication of The Korean Society of Wood Science and Technology has been served as a core of knowledges on wood science and technology. The Journal acts as a medium for the exchange of research in the area of science and technology related to wood, and publishes results on the biology, chemistry, physics and technology of wood and wood-based products. Research results about applied sciences of wood-based materials are also welcome. The Journal is published bimonthly, and printing six issues per year. Supplemental or special issues are published occasionally.

The abbreviated and official title of the journal is '*J. Korean Wood Sci. Technol.*'. All submitted manuscripts written in Korean or English are peer-reviewed by more than two reviewers. The title, abstract, acknowledgement, references, and captions of figures and tables should be provided in English for all submitted manuscripts. Some of the articles are indexed in Korea Citation Index (KCI) and SCOPUS.

All manuscripts should be submitted to the editorial office via the e-mail. The URL address of the Society is http://www.kswst.or.kr/. The URL address of Journal is http://www.kswst.or.kr/html/ sub03\_06.asp where full text is available. This journal was supported by the Korean Federation of Science and Technology Societies (KOFST) Grant funded by the Korean Government.

# Journal of The Korean Wood Science and Technology

Volume 44, Number 6, Printed on November 25, 2016

© All rights are reserved for The Korean Society of Wood Science and Technology.

Published by and Subscription Order to: The Korean Society of Wood Science and Technology c/o Department of Forest Products Korea Forest Research Institute (KFRI) 2nd Floor, Namu Byungwon-dong 57 Hoegi-ro, Dongdaemun-Gu Seoul 02455, Republic of Korea E-mail : wood@kswst.or.kr There is a charge for the subscription.

Printed by: Green Pine Media Inc. Tel: (02)2274-1128, Fax: (02)2266-4427 Original Article

# Effect of Phenol Formaldehyde Impregnation on The Physical and Mechanical Properties of Soft-Inner Part of Oil Palm Trunk<sup>1</sup>

Rudi Hartono<sup>2,†</sup> • Wahyu Hidayat<sup>3,4</sup> • Imam Wahyudi<sup>5</sup> • Fauzi Febrianto<sup>5</sup> • Wahyu Dwianto<sup>6</sup> • Jae-Hyuk Jang<sup>3</sup> • Nam-Hun Kim<sup>3,†</sup>

#### ABSTRACT

The objective of this study was to improve physical and mechanical properties of soft-inner part of oil palm trunk (S-OPT) after impregnation with phenol formaldehyde (PF) resin and densification by close system compression (CSC) method. Effect of different methods of PF resin impregnation (*i.e.*, no vacuum-pressure, vacuum, and vacuum-pressure) was evaluated. The results showed that PF resin impregnation and CSC significantly improved the physical and mechanical properties of S-OPT up to: (1) 176% in density; (2) 309% in modulus of rupture (MOR); (3) 287% modulus of elasticity (MOE); and (4) 191% in the compressive strength. Physical and mechanical properties of S-OPT showed their best performances when PF resin impregnated with vacuum-pressure method as shown by higher weight gain, density, MOR, MOE, compressive strength, and lower recovery of set due to better penetration of PF resin into S-OPT. Combining PF resin impregnation and densification by CSC method could be a good method to improve physical and mechanical properties of S-OPT.

Keywords: close system compression, phenol formaldehyde impregnation, physical and mechanical properties, soft-inner part of oil palm trunk

## 1. INTRODUCTION

Oil palm has developed into one of the most economically important plantation crops in Southeast Asia (Koh and Wilcove, 2007). Among countries in this region, oil palm industry in Indonesia was able to grow rapidly with the plantation expanding at an annual rate of more than 12% from 1990 to 2005 (Hashim *et al.*, 2012). In 2013, the total oil palm plantation in Indonesia stands at 10.46 million hectares, with more than 63% of the oil palm plan-

<sup>&</sup>lt;sup>1</sup> Date Received August 23, 2016, Date Accepted October 12, 2016

<sup>&</sup>lt;sup>2</sup> Faculty of Forestry, University of Sumatera Utara, Indonesia

<sup>&</sup>lt;sup>3</sup> Department of Forest Biomaterials Engineering, College of Forest and Environmental Sciences, Kangwon National University, Republic of Korea

<sup>&</sup>lt;sup>4</sup> Department of Forestry, Faculty of Agriculture, Lampung University, Indonesia

<sup>&</sup>lt;sup>5</sup> Department of Forest Products, Faculty of Forestry, Bogor Agricultural University, Indonesia

<sup>&</sup>lt;sup>6</sup> Research Center for Biomaterials, Indonesian Institute of Sciences, Indonesia

<sup>&</sup>lt;sup>†</sup> Corresponding author: Nam-Hun Kim (e-mail: kimnh@kangwon.ac.kr)

<sup>&</sup>lt;sup>†</sup> Corresponding author: Rudi Hartono (e-mail: rudihartono@usu.ac.id)

tations located in Sumatera Island and 30% are planted in Kalimantan Island (Directorate General of Estate Crops, 2014). The crude palm oil (CPO) production in 2013 peaked at 27.78 million tons, contributing to more than 50% of world production and positioned the country as the world's biggest producer of palm oil.

Oil palm trees have an economic life span of 24-26 years (Ismail and Mamat, 2002). After this age, it is usually felled for replanting due to decreased oil productivity. In Indonesia, 450,000 ha of oil palm plantation area are expected to be replanted annually during the next 25 years. Such large area will generate large amount of potential biomass particularly in the form of trunks. During replantation the land owners are face with a big problem of disposal of felled oil palm trunks (OPT). These biomasses are commonly dumped off by burning or lands filling which put significant negative impact on the environment due to pollution created. Therefore, the potential utilizations of OPT should be explored to develop productive uses for OPT and mitigating environmental problems from waste biomass.

Previous studies have reported properties of various panel products from OPT, such as sawntimber (Bakar *et al.*, 2006), particleboard (Nadhari *et al.*, 2013; Lamaning *et al.*, 2014), medium density fiberboard (Ibrahim *et al.*, 2014), laminated veneer lumber (Sulaiman *et al.*, 2009), and plywood (Abdul Khalil *et al.*, 2010a; Feng *et al.*, 2011; Hoong *et al.*, 2012). However the utilization of OPT as raw materials for such products limited by abrupt differences in physical and mechanical properties between the outer parts and inner parts of OPT. For example, Bakar et al. (1998) reported that the green moisture content (MC) of outer part was 258%, while the inner part was as high as 575%. Lim and Khoo (1986) stated that the density of OPT decreases linearly towards the center of the trunk, showing density values over twice those of the inner part. Previous studies revealed that only one-third of the OPT diameter and three-fourths of the height could be potentially used for light-weight building materials and furniture, while the remaining inner two-thirds of the trunk generally becomes waste due to its low dimensional stability (high moisture content, high shrinkage-swelling), low strength, low durability, and low machining properties (Bakar et al., 2006; Erwinsvah, 2008; Iswanto et al., 2010).

Densification by compression method is a promising method to improve the properties of the soft-inner part of oil palm trunk (S-OPT). In previous work, we have studied the densification of the inner part of S-OPT by close system compression (CSC) under different temperature and duration (Hartono et al., 2011; Hartono et al., 2016). The results showed that compression by the CSC method successfully increased the density, modulus of elasticity (MOE), modulus of rupture (MOR), and compressive strength of S-OPT up to 90%, 190%, 155%, and 120%, respectively (Hartono et al., 2016). The impregnation of phenol formaldehyde (PF) resin into OPT and wood has been reported to improve dimensional stability Rudi Hartono · Wahyu Hidayat · Imam Wahyudi · Fauzi Febrianto · Wahyu Dwianto · Jae-Hyuk Jang · Nam-Hun Kim

Properties	Unit	Value
pH (at 25℃)	-	12.55
Specific gravity (25℃)	-	1.20
Viscosity (at 25°C)	Poise	2.25
Gelation Time (at 135°C)	Min', Sec"	12'45"
Resin Content* (at 135°C)	%	42.50
Molecular weight	Mn	4000

Table 1. Properties of PF Resin

\* Non-volatile solid content

(Furuno *et al.*, 2004; Rowell, 2005), physical and mechanical properties (Shams *et al.*, 2006; Bakar *et al.*, 2013), and increased the resistance against fungal decay and termites attack (Nabil *et al.*, 2016). The use of PF resin for OPT impregnation has many advantages, such as low viscosity, lack of odor, low volatility, less heat generation at polymerization, good polymerization completion, and low in price (Abdul Khalil *et al.*, 2010b). To further improve the physical and mechanical properties of S-OPT, in this study we attempted to apply hybrid methods through the combination of PF resin impregnation and compression by CSC method.

## 2. MATERIALS AND METHODS

### 2.1. Materials

OPT was collected from 40-year-old plantation in Bogor, Indonesia. The samples of S-OPT were sawn into pieces of lumbers having dimensions of 150 mm  $\times$  50 mm  $\times$  20 mm in length, width, and thickness, respectively. To determine their initial density, samples were dried at 60 °C until they reached a constant weight, and then the weight and dimensions were measured. The average density of the samples after drying was  $0.34 \pm 0.01$  g/cm<sup>3</sup>.

Phenol formaldehyde (PF) resin was impregnated into the cell lumen of S-OPT. The PF resin was purchased from the Palmolite Adhesive Company in Indonesia. The properties of the PF resin used in this study are shown in Table 1.

### 2.2. Methods

# 2.2.1. PF resin impregnation and densification by CSC method

Before PF resin impregnation, a group of samples were hot-pressed to a compression ratio of 50% at 100°C for 4 h and another group of samples were not hot-pressed for comparison. Aqueous solution of 20% PF resin was prepared for impregnation. Three methods of PF resin impregnation were applied, including:

- No vacuum-pressure method: samples were soaked in the PF resin solution for 24 h, no vacuum or pressure was applied,
- Vacuum method: samples were soaked in the PF resin solution and vacuumed at 600 mmHg for 1 h,
- 3. Vacuum-pressure method: samples were

soaked in the PF resin solution and vacuumed at 600 mmHg for 1 h. Pressure of  $1 \text{ N/mm}^2$  for 30 min was then applied.

Four samples were used for each treatment. After PF resin impregnation, curing was performed in an oven-dryer at  $60^{\circ}$ C for 15 hours.

The samples were then compressed by CSC method. CSC is a compression method to improve permanent fixation of compressive deformation in a short time by hygrothermal treatment using moisture in wood or other lignocellulosic materials (Inoue et al., 1993). Detail description of the CSC method can be seen in our previous publication (Hartono et al., 2016). The samples were compressed with a target compression ratio of 50% at 135°C. After 10 min, hot water vapor inside CSC frame was released and then the compression process was continued for another 10 min. After compression by CSC method, the samples were conditioned under a relative humidity of 70  $\pm$ 5% at 25  $\pm$  2°C for 2 weeks before further testing. The final size of the samples after compression was 150 mm × 50 mm × 10 mm in length, width, and thickness, respectively.

#### 2.2.2. Physical properties evaluation

The air-dry density of samples after PF resin impregnation and compressed by CSC method was determined by measuring their air-dry weight and volume using sample dimensions of 20 mm × 20 mm × 10 mm. Weight gain percentage (WG%) was determined by measuring samples weight before impregnation ( $w_o$ ) and weight after PF resin impregnation ( $w_i$ ), and then calculated using the equation:

$$WG (\%) = \frac{w_i - w_o}{w_o} \times 100\% \dots (1)$$

The anatomical structure after PF resin impregnation and compression by CSC was observed. Sliding microtome was used to make sections with 30  $\mu$ m in thickness. The sections were stained with Safranin-Astra blue, dehydrated in a graded series of alcohol solutions (50%, 70%, 90%, 95%, and 99%), mounted in Canada balsam, and observed with an optical microscope (Nikon Eclipse E600, Japan).

The recovery of set (RS) was obtained using samples with dimensions of 30 mm  $\times$  20 mm  $\times$ 10 mm by soaking the samples in room-temperature water (20 ± 3 °C) for 24 h and then in hot water (100 ± 3 °C) for 30 min (Dwianto *et al.*, 1999). The RS was calculated as follows:

$$RS (\%) = \frac{T_r - T_c}{T_o - T_c} \times 100\% \dots (2)$$

where  $T_{\rm o}$  is the initial thickness,  $T_{\rm c}$  is the thickness after compression, and  $T_{\rm r}$  is the thickness after recovery. All the dimensions of the samples were measured in the oven-dry condition.

#### 2.2.3. Mechanical properties evaluation

Modulus of rupture (MOR), modulus of elasticity (MOE), and compressive strength tests were conducted using a universal testing machine (Model 4482, Instron, USA). The sample dimensions for the MOR and MOE tests were  $150 \text{ mm} \times 10 \text{ mm} \times 10 \text{ mm}$ . Three-point bending was applied over an effective span of 100 mm at a loading speed of 5 mm/min. The Rudi Hartono · Wahyu Hidayat · Imam Wahyudi · Fauzi Febrianto · Wahyu Dwianto · Jae-Hyuk Jang · Nam-Hun Kim

Immussion mathed	WG (%)		Density (g/cm <sup>3</sup> )		RS (%)	
	Without HP	With HP	Without HP	With HP	Without HP	With HP
Control	-		0.34 <sup>A</sup> (0.01)	-	-	
No vacuum-pressure	11.52 <sup>A</sup>	10.59 <sup>A</sup>	0.70 <sup>BC</sup>	0.66 <sup>B</sup>	40.25 <sup>D</sup>	26.11 <sup>C</sup>
	(2.47)	(2.12)	(0.04)	(0.06)	(6.40)	(6.78)
Vacuum	28.37 <sup>C</sup>	17.39 <sup>B</sup>	0.77 <sup>DC</sup>	$0.72^{BCD}$	3.56 <sup>A</sup>	13.55 <sup>B</sup>
	(2.90)	(2.60)	(0.04)	(0.05)	(1.40)	(2.24)
Vacuum-pressure	50.94 <sup>E</sup>	36.68 <sup>D</sup>	0.94 <sup>E</sup>	0.80 <sup>D</sup>	1.92 <sup>A</sup>	2.50 <sup>A</sup>
	(6.38)	(4.01)	(0.06)	(0.07)	(0.34)	(1.33)

Table 2. Physical properties of S-OPT after impregnation with PF and compression by CSC method

Notes: HP: hot pressing prior to PF resin impregnation; means within a parameter (two columns) followed by the same capital letter are not significantly different at 1% significance level using Duncan's multiple range test. Numbers in parenthesis are standard deviations.

dimensions of the samples for the compressive strength test were 40 mm  $\times$  10 mm  $\times$  10 mm. The MOR, MOE, and compressive strength (*R*) were calculated as follows:

$$MOR \ (N/mm^2) = \frac{3 \times P \times L}{2 \times b \times t^2} \dots (3)$$

$$MOE \ (N/mm^2) = \frac{P_p \times L^3}{4 \times Y_p \times b \times t^3} \cdots \cdots (4)$$

where *P* is the maximum load (N),  $P_p$  is the load at the proportional limit (N),  $Y_p$  is the deflection (mm), *L* is the span length (mm), *b* is the sample width (mm), and *t* is the sample thickness (mm).

#### 2.2.4. Data analysis

The experimental design was a completely randomized design (CRD). The results of the properties tested were submitted to an overall analysis of variance (ANOVA) using SPSS version 16.0. The homogeneity of the means among combinations was tested using the Duncan's Multiple Range Tests.

## 3. RESULTS AND DISCUSSION

### 3.1. Physical properties

Physical properties of S-OPT before and after PF resin impregnation and CSC are shown in Table 2. The results showed that the WG and density of samples without hot pressing was significantly higher than samples with hot pressing prior to PF resin impregnation, and the results were consistent for all three impregnation methods. Hot pressing prior to PF resin impregnation made the S-OPT structure become more compact, resulting in the difficulty for PF resin to penetrate. For impregnation method with no vacuum-pressure, samples with hot pressing showed lower RS compared to samples without hot pressing prior to PF resin impregnation. However, when using vacuum and vacuum-pressure impregnation methods, the samples with hot-pressing showed significantly higher RS than samples without hot pressing. Lower RS indicated better dimensional stability and better fixation.

The combination of PF resin impregnation

Effect of Phenol Formaldehyde Impregnation on The Physical and Mechanical Properties of Soft-Inner Part of Oil Palm Trunk



Fig. 1. Soft-inner part of oil palm trunk (S-OPT) used for this study.

and CSC of S-OPT resulted in higher density achieved compared to only CSC. The combination of PF resin impregnation and CSC increased the S-OPT density by 94-176%, significantly higher than the increase of density by using only CSC of 3-90% (Hartono *et al.*, 2016).

The PF resin impregnation method (i.e., without hot-pressing and with vacuum-pressure) of S-OPT resulted in the highest WG and density with the lowest RS. The values indicated that the treatment resulted in a better the PF resin penetration, higher compression ratio, better distability, better fixation. mensional and Vacuum-pressure method resulted in better WG, density, and RS in both samples without and with hot-pressing prior to PF resin impregnation. In addition, statistical analyses showed that WG and density of S-OPT treated without hot-pressing prior to PF resin impregnation were significantly higher than S-OPT treated with hot-pressing, while RS values showed no significantly different.



Fig. 2. Micrographs of S-OPT at (A) transverse section and (B) radial section: PF impregnated parenchymatous ground tissue and vessels of S-OPT ( $20 \times$  magnification).

During vacuum-pressure, vacuum could evacuate the air inside of S-OPT, and pressure forced PF resin to penetrate into S-OPT. The pressure may opened up parenchyma and vessel, and it makes PF resin easier to enter, hence the WG value was the higher. Vessels and parenchyma cells filled out with PF resin and after compression by CSC method can be seen in Fig. 2.

Similar to wood, OPT is a hygroscopic material. The hydrophilic properties of OPT

Rudi Hartono · Wahyu Hidayat · Imam Wahyudi · Fauzi Febrianto · Wahyu Dwianto · Jae-Hyuk Jang · Nam-Hun Kim

Impregnation method	MOR (N/mm <sup>2</sup> )		MOE (N/mm <sup>2</sup> )		Compressive strength (N/mm <sup>2</sup> )	
	Without HP	With HP	Without HP	With HP	Without HP	With HP
Control	12.08 <sup>A</sup> (1.16)	-	1191.26 <sup>A</sup> (64.06)	-	7.80 <sup>A</sup> (0.96)	-
No vacuum-pressure	37.75 <sup>BC</sup>	35.24 <sup>B</sup>	2882.89 <sup>BC</sup>	2479.98 <sup>B</sup>	16.65 <sup>BC</sup>	14.32 <sup>B</sup>
	(3.17)	(2.30)	(366.15)	(273.88)	(2.15)	(1.89)
Vacuum	42.37 <sup>D</sup>	40.96 <sup>CD</sup>	3861.00 <sup>D</sup>	3204.00 <sup>C</sup>	18.69 <sup>C</sup>	15.86 <sup>B</sup>
	(1.83)	(3.10)	(200.01)	(546.62)	(0.74)	(1.61)
Vacuum-pressure	49.47 <sup>E</sup>	44.81 <sup>D</sup>	4615.94 <sup>E</sup>	4187.68 <sup>DE</sup>	22.75 <sup>D</sup>	21.37 <sup>D</sup>
	(2.87)	(2.93)	(443.91)	(217.94)	(1.45)	(2.01)

Table 3. Mechanical properties of OPT after impregnation with PF and compression by CSC method

Notes: HP: hot pressing prior to PF resin impregnation; means within a parameter (two columns) followed by the same capital letter are not significantly different at 1% significance level using Duncan's multiple range test. Numbers in parenthesis are standard deviations.

may be caused by its thin cell walls and large lumens (Erwinsyah ,2008, Abdul Khalil *et al.*, 2008). The S-OPT became moisture-resistant by the polymerization of the cured resins; hence more PF resin penetration or higher WG resulted in the increase of dimensional stability as shown by an increase of density and reduction of RS. The results were in agreement with previous studies. Furuno *et al.* (2004) reported an increase of dimensional stability of wood and bamboo after impregnation of PF resin. Gabrielli and Kamke (2008) stated that PF resin impregnation contributed to an increase of dimensional stability and reduction of thickness-swelling of wood.

## 3.2. Mechanical properties

The control sample of S-OPT had MOE of 12.08 N/mm<sup>2</sup> and compressive strength of 7.8 N/mm<sup>2</sup> and classified as very poorly strong (Strength Class V) according to Indonesian Standard SNI 01-0608-1989 (BSN, 1989). The

PF resin impregnation with vacuum-pressure method could increase the MOR strength class into Strength Class III (moderately strong) and compressive strength into Strength Class IV (poorly strong). Overall results showed that the impregnation of PF resin and compression by CSC method significantly increased mechanical properties of S-OPT by 191-309%, 108-287%, and 83-191% for MOR, MOE, and compressive strength, respectively (Table 3). The increase of mechanical properties using the combination of PF resin impregnation and CSC of S-OPT was higher than that using only CSC with MOE, MOR, and compressive strength of 43-192%, 14-155%, 19-123%, respectively (Hartono et al., 2016).

Table 3 shows that S-OPT treated without hot-pressing prior to PF resin impregnation had better mechanical properties than that of S-OPT treated with hot-pressing. The MOR, MOE, and compressive strength increased in order after the sample treated with no vacuum-pressure, vacuum, and vacuum-pressure, respectively with



**Fig. 3.** Weight gain of S-OPT after PF resin impregnation and compression by CSC versus: (a) MOR, (b) MOR, and (c) compressive strength.

the highest value achieved by S-OPT treated with vacuum-pressure method.

Mechanical properties were attributable to WG value. The higher WG resulted in the higher MOR, MOE, and compressive strength. Fig. 3 shows the relationship between WG with mechanical properties. The regression analysis showed that the correlation between WG and MOR could be described by power fit, while the relationship between WG and MOE, WG and compressive strength could be described by a second-order polynomial.

## 4. CONCLUSION

The S-OPT was impregnated by PF resin and compressed by CSC method. PF resin impregnation by no vacuum-pressure, vacuum, and vacuum-pressure method significantly improved physical and mechanical properties of compressed OPT. The assessed physical and mechanical properties showed their best performances when PF resin impregnated with vacuum-pressure method. Combining PF resin impregnation and compression by CSC method could be a good method to improve physical and mechanical properties of soft inner part of OPT.

## ACKNOWLEDGEMENT

This work was supported by the fund under the framework of international cooperation program managed by National Research Foundation of Korea (2015K2A1A2070699).

## REFERENCES

Abdul Khalil, H.P.S., Nurul Fazita, M.R., Bhat, A.H., Jawaid, M., Nik Fuad, N.A. 2010a. Development and material properties of new hybrid plywood from oil palm biomass. Materials and Design 31: 417~424. Rudi Hartono · Wahyu Hidayat · Imam Wahyudi · Fauzi Febrianto · Wahyu Dwianto · Jae-Hyuk Jang · Nam-Hun Kim

- Abdul Khalil, H.P.S., Bhat, A.H., Jawaid, M., Amouzgar, P., Ridzuan, R., Said, M.R. 2010b. Agro-wastes: Mechanical and physical properties of resin impregnated oil palm trunk core lumber. Polymer Composites 31(4): 638~644.
- BSN (Badan Standarisasi Nasional). 1989. Physical and mechanical properties requirement of wood for furniture. Jakarta, Indonesia. National Standardization Agency.
- Bakar, E.S., Rachman, O., Hermawan, D., Karlinasari, L., Rosdiana, N. 1998. Utilization of oil palm tree as building and furniture materials (1): Physical and chemical properties and durability of oil palm wood. Jurnal Teknologi Hasil Hutan 11(1): 1~12.
- Bakar, E.S., Febrianto, F., Wahyudi, I., Ashaari, Z. 2006. Polygon sawing: An optimum sawing pattern for oil palm stems. J. Biol. Sci. 6(4): 734~ 749.
- Bakar, E.S., Tahir, P.M., Sahri, M.H., Mohd Noor, M.S., Zulkifli, F.F. 2013. Properties of Resin Impregnated Oil Palm Wood (*Elaeis Guineensis* Jack). Pertanika J. Trop. Agric. Sci. 36(S): 93~ 100.
- Directorate General of Estate Crops. 2014. Tree crop estate statistics of Indonesia 2013-2015: Palm oil. Directorate General of Estate Crops. Jakarta, Indonesia. http://ditjenbun.pertanian.go.id/tinymc puk/gambar/file/statistik/2015/SAWIT%202013% 20-2015.pdf
- Dwianto, W., Morooka, T., Norimoto, M., Kitajima, T. 1999. Stress relaxation of Sugi (*Cryptomeriajaponica* D. Don) wood in radial compression under high-temperature steam. Holzforschung 53(5): 541~546.
- Erwinsyah. 2008. Improvement of Oil Palm wood properties using bioresin. PhD thesis. Technische Universität Dresden.
- Feng, L.Y., Tahir, P.M., Hoong, Y.B. 2011. Density

distribution of Oil Palm stem veneer and its influence on plywood mechanical properties. Journal of Applied Sciences 11(5): 824~831.

- Furuno, T., Imamura, Y., Kajita, H. 2004. The modification of wood by treatment with low molecular weight phenol-formaldehyde resin: a properties enhancement with neutralized phenolic-resin and resin penetration into wood cell walls. Wood Science and Technology 37(5): 349~361.
- Gabrielli, C., Kamke, F.A. 2008. Treatment of chemically modified wood with VTC process to improve dimensional stability. Forest Product Journal 58(12): 82~86.
- Hartono, R., Wahyudi, I., Febrianto, F., Dwianto, W. 2011. Maximum compression level measurement of oil palm trunk. Jurnal Ilmu dan Teknologi Kayu Tropis 9(2): 173~183.
- Hartono, R., Wahyudi, I., Febrianto, F., Dwianto, W., Hidayat, W., Jang, J.H., Lee, S.H., Park, S.H., Kim, N.H. 2016. Quality Improvement of Oil Palm Trunk Properties by Close System Compression Method. Journal of the Korean Wood Science and Technology 44(2): 172~183.
- Hashim, K., Tahiruddin, S., Asis, A.J. 2012. Palm and palm kernel oil production and processing in Malaysia and Indonesia, in: Palm Oil: Production, Processing, Characterization, and Uses, Lai, O.M., Tan, C.P., Akoh, C.C. (eds.), AOCS Press, Urbana, IL.
- Hoong, Y.B., Loh, Y.F., Nor hafizah, A.W., Paridah, M.T., Jalaluddin, H. 2012. Development of a new pilot scale production of high grade oil palm plywood: Effect of pressing pressure. Materials and Design 36: 215~219.
- Ibrahim, Z., Aziz, A.A., Ramli, R., Mokhtar, A., Omar, R., Lee, S.J. 2014. Production of Medium Density Fibreboard (MDF) from Oil Palm Trunk (OPT). Journal of Applied Sciences 14: 1174~ 1179.

Effect of Phenol Formaldehyde Impregnation on The Physical and Mechanical Properties of Soft-Inner Part of Oil Palm Trunk

- Inoue, M., Kadokawa, N., Nishio, J., Norimoto, M. 1993. Permanent fixation of compressive deformation by hygro-thermal treatment using moisture in wood. Wood Res Bull. 29: 54~61.
- Ismail, A., Mamat, M.N. 2002. The optimal age of oil palm replanting. Oil Palm Industry Economic Journal 2(1): 11~18.
- Iswanto, A.H., Sucipto, T., Azhar, I., Coto, Z., Febrianto, F. 2010. Physical and Mechanical Properties of Palm Oil Trunk from Aek Pancur Farming-North Sumatera. Jurnal Ilmu dan Teknologi Hasil Hutan 3(1): 1~7.
- Koh, L.P., Wilcove, D.S. 2007. Cashing in palm oil for conservation. Nature 448: 993~994.
- Lamaning, J., Hashim, R., Sulaiman, O., Sugimoto, T., Sato, M., Hiziroglu, S. 2014. Measurement of some properties of binderless particleboards made from young and old oil palm trunks. Measurement 47: 813~819.
- Lim, S.C., Khoo, K. 1986. Characteristic of oil palm trunk and its potential utilization. Malaysian Forester 49(1): 3~22.
- Nabil, F.L, Zaidon, A., Anwar, U.K.M., Bakar, E.S., Lee, S.H., Paridah, M.T. 2016. Impregnation of

Sesenduk (*Endospermum diadenum*) Wood with Phenol Formaldehyde and Nanoclay Admixture: Effect on Fungal Decay and Termites Attack. Sains Malaysiana 45(2): 255~262.

- Nadhari, W.N.A.W., Hashim, R., Sulaiman, O., Sato, M., Sugimoto, T., Selamat, M.E. 2013. Utilization of Oil Palm trunk waste for manufacturing of binderless particleboard: Optimization study. BioResources 8(2): 1675~1696.
- Rowell, R. 2005. Chemical Modification of Wood. In: Rowell RM (ed.) Handbook of Wood Chemistry, Wood Composites, Chap. 14. CRC Press, Boca Raton, p. 381~420.
- Shams, M.I., Yano, H., Endou, K. 2006. Compressive Deformation of Wood Impregnated with Low Molecular Weight Phenol Formaldehyde (PF) Resin III: effects of sodium chlorite treatment. J. Wood Sci. 51: 234~238.
- Sulaiman, O., Salim, N., Hashim, R., Yusof, L.H.M., Razak, W., Yunus, N.Y.M., Hashim, W.S., Azmy, M.H. 2009. Evaluation on the suitability of some adhesives for laminated veneer lumber from oil palm trunks. Materials and Design 30(9): 3572~3580.

학회소식

# 2016 대한민국 산림문화박람회 홍보 부스 운영

- □ 주 제 : 숨과 쉽이 함께하는 웰니스의 향연
- □ 일 시 : 2016년 10월 21일(금) ~ 10월 30일(일)
- □ 장 소 : 충남 예산군 덕산온천 관광지구 일원
- □ 주요내용 : 공식행사, 전시, 산림 및 온천 체험, 임산물시장,
   산림경영 컨설팅, 공연, 국화 전시

회원소식

· 김광철 이사, 목조주택 설계 가이드 출판. 전북대학교출판문화원. ISBN 978-89-98534-93-6 (2016. 8. 31)
· 박상범 상임이사, 제19회 농림축산식품과학기술대상 대통령상 수상(2016. 10. 19.)

○ 조남석 고문, 제4회 현신규학술상 대상 수상(2016. 10. 21)

○ 한규성 상임부회장, 제15회 산의날 근정포장 수상(2016. 10. 18)

# **Instruction to Authors**

Authors are requested to carefully abide by the 'Instruction to Authors' to ensure that reviewing and publication process of the manuscript be properly handled in a due course. Manuscript will be returned to the author if it is not properly presented according to the following instructions.

#### **Types of Publications**

The Journal publishes original article, short note, communication, and review article. The original article should be a comprehensive report containing significant new research data and/or new interpretations of existing data with special emphasis on industrial applications.

#### **Research Ethics Policy**

Manuscripts submitted to the Journal are not copyrighted, published, or submitted elsewhere, except in abstract form. Review articles should provide critical surveys of progresses in a specific field of science, engineering, or technology related to wood. For the policies on the research and publication ethics not stated in this instructions, International standards for editors and authors (http://publicationethics. org/international-standards-editors-and-authors) can be applied. And the corresponding author should submit the Declaration of Ethical Conduct in Research and Publication.

#### Process of a Disciplinary Action

When a disciplinary action is recommended by the ethics committee, the chairman should convene a board meeting to determine whether or not to take any disciplinary action. A warning, suspension or dismissal of a membership can be applied to the member who has violated ethical policy. The result of the final decision may be made public if necessary. When the manuscript submitted is proved to have committed misconduct in its research, the editorial board should reject or withdraw it. The author should be banned of submitting a manuscript to this journal for three years from the time of decision.

#### Submission and Inquiry

Manuscript that contains all texts (title page, abstract, body of the article, captions, and references) and tables should be one file in a format of Microsoft Word for Windows or Hangul (Korean Word Processor). Name the file with the corresponding author's name. Do not include any page-layout instructions such as graphics placement. Carriage returns should be used only to end headings and paragraphs, and the auto-hyphenation should be turned off. Tables may be created using text mode or table format; the latter is preferred.

Submission of electronic illustrations is encouraged, but not required. Each illustration (figure, scheme, etc.) should be in a separate file. The file should be named descriptively; e.g. Figure 1 or Figure 2.

Authors are requested to submit the manuscript via e-mail, and to send any inquiry to the Editorial Office shown below:

Editorial Office of The Korean Society of Wood Science and Technology c/o Department of Forest Products Korea Forest Research Institute (KFRI) 2nd Floor, Namu Byungwon-dong 57 Hoegi-ro, Dongdaemun-Gu Seoul, 130-712, Republic of Korea Tel: +82-2-877-4781 Fax: +82-2-877-4780 E-mail: kswstwood@gmail.com

#### **Review and Revisions**

All contributions are reviewed by two or more peer referees to ensure both accuracy and relevance, and revisions may thus be required. Reviewers make decision on the review of a manuscript upon four categories: 1) Accept without revision, 2) Accept with minor revision, 3) Accept with major revision and re-review, and 4) Reject.

When a manuscript is sent back to an author for the revision, the revised version should be returned with 'Response to Reviewer's Comments', specifying changes made in the revision as soon as possible after the corresponding author receives the reviewers' reports. Revised manuscript that is not returned in two (2) months is considered withdrawn. A formal notification will be sent to the corresponding author after the manuscript has been accepted for publication.

#### Preparation of Manuscripts

All manuscripts must be written in clear and concise either in Korean or English, typewritten, double-spaced, on one side of A4 paper with adequate margins and proper page number at every sheet of paper.

#### Arrangement

Manuscript is arranged in the following order. Each starts on a new sheet.

1. Title Page.

Manuscript title, author's name, and affiliation. The corresponding author(s) should be clearly indicated with cross (+). The affiliation should comprise the department, institution, city, postal code, and nation. Please also suggest an abbreviated title limited to 80 characters (including spaces) for running head.

2. Abstract.

An abstract that contains less than 250 words must be provided with all types of manuscripts. The abstract outlines in a single paragraph the aims, scope, methods, significant findings, and conclusions of the contribution. Provide less than seven keywords that best represent the content of the paper.

3. The Text.

Suitably divided under such headings as Introduction, Experimental, Results and Discussion, and Conclusions.

- 4. Acknowledgment(s) (if any).
- 5. References (and Notes, if any).
- 6. Tables. Each on a separate sheet.
- 7. Captions for Illustrations.
- 8. Illustrations.

Each on a separate sheet containing no text. Labeled with the author's name and illustration number.

9. Appendix (if any).

#### Nomenclature and Units

Each paper should be consistent within itself as to abbreviations, symbols, and units. Authors should use SI units wherever possible. Nomenclature should conform to that recommended by the International Union of Pure and Applied Chemistry and Chemical Abstracts Service.

#### Equations and Formulae

Complicated chemical equations, formulae, and schemes should be presented as furnished artwork. Mathematical expressions and chemical formulae should be typed with available symbols and letters. Capital, lower case, and Greek letters should be easily discernible, and identified in the margin so that ambiguities could be protected. Equations should be numbered consecutively throughout the paper with Arabic numerals in parentheses placed flush right, and should be thusly referred to in the text [such as Equation (2)].

#### Tables

Tables should be numbered in Arabic numerals in

the order of mention in the text. A table should have a descriptive title (above the table) and appropriate column headings. Avoid tables and graphs that involve duplication. If you use a graph, do not include a table of the same data: If the readers need a table, omit the graph. Present a few representative results for lengthy table when practical.

#### Illustrations

Figures and graphs should be carefully prepared in either black and white, or color. Figures and graphs in color could be printed in a PDF format at the web site. However, printing those in a hardcopy will result in an extra page charge. It should be of sufficient size so that after photo-reproduction to a single-column width (8 cm) the smallest letter could be 2 mm. Legend should be placed in a proper space of the drawings, not in the caption, whenever possible. Original copies of the graphs, drawings, and photographs should be numbered in Arabic numerals in the order of mention in the text, and included at the end of the manuscript.

#### Photographs

Photographs are accepted with additional charge. The current charge for the processing of photographs is 2,500 Won or equivalent per each black-and-white photograph and 20,000 Won or equivalent per each color photograph.

#### **References (and Notes)**

All references and explanatory notes, if any, should be cited within the text by authors last name and year of publication in parentheses. In the case of more than two authors, only the first author is listed, e.g. (Hill *et al.*, 2009).

An alphabetical order of all the cited references and notes should be listed according to the first authors' name, together with the title of the paper, the full journal title, and the full quotation of the bibliographical reference at the end of the text. Examples of bibliographic references are given below: <Articles in journals>

- Konnerth, J., Gindl, W. 2006. Mechanical characterisation of wood-adhesive interphase cell walls by nanoindentation. Holzforschung 60(4): 429~433.
- Kisser, J.G., Ylinen, A., Freudenberg, K., Kollmann, F.F.P., Liese, W., Thunell, B., Winkelmann, H.G., Côté Jr., W.A., Koch, P., Marian, J.E., Stamm, A.J. 1967. History of wood science. Wood Science and Technology 1(3): 161~190.

Examples of reference citation in the text:

- Two authors only: (Konnerth and Gindl, 2006)
- More than three authors: (Kisser et al., 1967)

#### <Books and Book Chapter>

- Fengel, D., Wegener, G. 1984. Wood: Chemistry, Ultrastructure, Reactions. De Gruyter, Berlin, Germany.
- Tanem, B.S., Kvien, I., van Helvoort, A.T.J. 2006. Morphology of Cellulose and Its Nanocomposites. In: Cellulose Nanocomposites: Processing, Characterization, and Properties, ACS Symposium Series 938, Ed. by Oksman, K. and Sain, M., American Chemical Society, Washington DC, USA.

<Conference Papers>

Walford, G.B. 2003. Research and wood industry in Australia and New Zealand. In: Lee, H.-H. and Jang, S.-S., (eds), Daejeon, Republic of Korea, Proc. of 11th the International Association of Wood Products Societies (IAWPS 2003), pp. 3~13.

#### <Thesis>

Lyons, C.K. 2001. Mechanical stresses in trees resulting from strain compatibility in an anisotropic material. Ph.D. Thesis, Oregon State University, USA.

Any queries regarding accepted papers, proofs or reprints should be directed to the same address.

#### **Proofs and Reprints**

Galley proofs, original manuscript, cut copy, and Reprint Order Form are sent by the Society directly to the corresponding author. The attention of the author is directed to the instruction which accompanies the proof, especially the requirement that all corrections, revisions, and additions should be entered on the proof and not on the manuscript. Proofs should be checked against the manuscript (in particular all tables, equations, and formulae, since this is not done by the editorial board), and returned as soon as possible.

Authors are entitled 30 free reprints of the article. Should the author needs additional reprints, the filled-out Reprint Order Form must be returned with the payment.

#### Page Charges

Page charges defray a part of the cost of publication. The bill is issued with the shipment of the reprints. The current charge is 80,000 Won for 6 printed pages, and 40,000 Won/printed page for more than 6 printed pages.

## **Checklist for Authors**

Title of the manuscript submitted:

Please check below items as 🗸 mark before the submission of the manuscript.

#### 1. General guidelines

- □ The manuscript submission contains one original main text manuscript (Figure, Table or Images included) and author's checklist should be dispatched to the Editorial Office via email (Statement of copyright transfer should be dispatched in a PDF format file after the end of reviewing process).
- □ Manuscript should be typed in Korean or English using word processor with a space of 30 mm from upper, lower, left and right main, 10.0 pt in font size, and line space of 180%.
- □ The main text consists of title page, abstract, main text, references, tables and figures, which are properly placed throughout the main text.
- □ The main text consists of INTRODUCTION, MATERIALS AND METHODS, and RESULTS AND DISCUSSION, CONCLUSION, and REFERENCES.

#### 2. Title page

- □ Title, name of author and affiliation is written both in English and Korean, while all these should be written in English for the article that is expected to be published in English issue.
- □ The title page should provide the name, address, e-mail, telephone, and fax of the corresponding author.

#### 3. Abstract and Keywords

- $\hfill\square$  The abstract is supposed to be less than 250 words.
- $\hfill\square$  Less than seven keywords should be provided with the manuscript.

#### 4. Main text

- □ The order of the subtitle is described according to the Instruction to Authors.
- □ References in the main text are described according to the Instruction to Authors.

#### 5. References

- □ Every article in REFERENCES should be cited in the main text.
- □ References are cited the author's name and publication year as described in the Instruction to Authors.
- □ All references should be written in English, and listed by the same format as the Instruction to Authors.

#### 6. Tables, figures, or Images

- □ The titles and legends of the tables and figures should be written in English.
- □ Photos and images should have high quality enough to publication.

## Statement of Copyright Transfer

To: Editor-in-Chief of the Journal of The Korean Wood Science and Technology

Title of the manuscript submitted:

I hereby certify that I agree to submit the manuscript entitled as the above to Journal of The Korean Wood Science and Technology by abiding the following statements;

- □ This manuscript is original and there is no copyright problem, defamation and privacy intrusion. Any legal or ethical damage should not be directed to The Korean Society of Wood Science and Technology due to this manuscript.
- □ All authors made actual contribution to the manuscript in terms of scientific aspects, and were equally responsible for the manuscript.
- □ This manuscript was not published or considered for publication to any other scientific journals in the world. It will not be submitted again to other journals without permission from Editor-in-Chief of the Journal of The Korean Wood Science and Technology if it is accepted for publication.
- □ Copyright of this manuscript shall be transferred to The Korean Society of Wood Science and Technology if it is published in the Journal of The Korean Wood Science and Technology. It means that if any persons including authors want to use the contents of this manuscript, they should obtain the permission from the Society and the source of contents cited should be properly clarified.

Date:

Signature

#### **Disclosure Statement of Conflicts of Interests**

List any potential conflicts of interests of this manuscript (any financial support or benefits have been received by the author(s) that could affect the work reported in the article) or indicate "None".

# Declaration of Ethical Conduct in Research and Publication

Title:

	Name	Affiliation	Contact Information
Corresponding Author			Address: Tel: E-mail:

On the behalf of all authors, and as a corresponding author of the above manuscript submitted to the Journal of The Korean Wood Science and Technology, hereby, I swear that I follow the research ethics policy of The Korean Society of Wood Science and Technology, and I do not commit research misconduct as falsification, distortion of research findings, or plagiarism which damages any academic and ethical integrity, by declaring this ethical conduct in research and publication.

I am also declaring to accept the decision by the Editorial Board Members of The Korean Society of Wood Science and Technology if any misconduct occurs at any stage of the above mentioned research work.

Date:

Corresponding author:

(signature)

# Journal of The Korean Wood Science and Technology (Vol. 44, No. 6)

Editor-in-Chief	PARK, Byung-Dae (Kyungpook National University)		
Associate Editor	ROH, Jung-Kwan (Gyeongnam National University of Science and Technology)		
Editorial Board Members	JEONG, Gi Young (Chonnam National University) KANG, Seog Goo (Chungnam National University) KIM, Birm-June (Kookmin University) LEE, Seung-Hwan (Kangwon National University) LEE, Sun-Young (Forest Research Institute, Korea) LEE, Yang Soo (Chonbuk National University) PARK, Han-Min (Gyeongsang National University) PARK, Joo-Saeng (Forest Research Institute, Korea) SHIN, Soo-Jeong (Chungbuk National University) YEO, Hwanmyeong (Seoul National University)		
Editorial Assistant	SUR, Sang-Hee (The Korean Society of Wood Science and Technology)		
Editing Manager	PARK, Pyeong (Keuk Dong Design & Communication Co., Ltd)		
International Editorial Board Member	DUFRESNE, Alain (Grenoble Institute of Technology, France) DUNKY, Manfred (Kronospan GmbH Lampertwalde, Germany) ENDO, Takashi (National Institute of Advanced Industrial Science and Technology, Japan) EVANS, Philip (University of British Columbia, Canada) FRIHART, Chuck R. (Forest Products Laboratory, USA) HADI, Yusuf Sudo (Bogor Agricultural University, Indonesia) LABBE, Nicole (University of Tennessee. USA) NIEMZ, Peter (Swiss Federal Institute of Technology (ETH), Switzerland) RAGAUSKAS, Arthur (Georgia Institute of Technology, USA) SAKA, Shiro (Kyoto University, Japan) SCHMITT, Uwe (Johann Heinrich von Thunen Institute (vTI), Germany) SINGH, Adya P. (SCION, New Zealand) SMITH, Greg (University of British Columbia, Canada) SUGIYAMA, Junji (Kyoto University, Japan) TOHMURA, Shin-ichiro (Forestry and Forest Products Research Institute, Japan) WONG, Andrew (University Malaysia Sarawak, Malaysia) YIN, Yafang (Chinese Academy of Forestry, China)		

This Journal was supported by the Korean Federation of Science and Technology Societies Grant funded by the Korean Government (KFSTS).

## Published by THE KOREAN SOCIETY of WOOD SCIENCE & TECHNOLOGY Volume 44, Number 6

Printed on November 22, 2016 Issued on November 25, 2016

Publisher: Kim, Nam-Hun

Editor: Park, Byung-Dae

#### Contact

Tel: (+82)-2-877-4781 Fax: (+82)-2-877-4780

**Printed by** Keuk Dong Design & Communication Co., Ltd Tel: (+82)-2-2274-7800 Fax: (+82)-2-2266-4427

## Submission to:

Editor-in-Chief, Byung-Dae Park 2<sup>nd</sup> Fl., Namoo Byungwondong, Korea Forest Research Institute, Seoul, 02455 Tel: (+82)-2-877-4781 Fax: (+82)-2-877-4780 E-mail: kswstwood@gmail.com

#### Publisher: Nam-Hun Kim

Department of Forest Biomaterials Engineering College of Forest and Environmental Sciences, Kangwon Natioanl University, Chuncheon, 24341 Tel: (+82)-33-250-8327 Fax: (+82)-33-256-8320 E-mail: wood@kswst.or.kr