



Plagiarism Checker X Originality Report

Similarity Found: 5%

Date: Senin, Desember 16, 2019

Statistics: 118 words Plagiarized / 2457 Total words

Remarks: Low Plagiarism Detected - Your Document needs Optional Improvement.

INSIST Vol. 2 No. 2, April 2018 (89 – 92) <http://insist.unila.ac.id/> DOI:10.23960/ ins. v2i2. 8 7 Received: 02/06/2017 Accepted: 10/08/2017 Published online: 20/10/2017 eISSN: 2502-8588 The Effect Catalyst Natural Zeolite of Lampung On The Synthesis Of -Terpineol From Turpentine Herti Utami^{1*}, Simparmin Br. Ginting¹, Dwi Derti Sulistiowati¹ and Ria Putri Hermiyati¹ A b s t r a c t — The major component of turpentine is a -pinene. Alpha ine e yd sinanacidcatalyst roce - terpeneol. It can be used as a perfume, anti -insect, and disinfectants.

The using of heterogeneous catalysts as natural zeolite can be a new alternative to replacehomogeneous catalysts. The purpose of this study was to determine the effect of zeolite catalysts and the reaction time which resulting the highest coversio n ydoreactis f rptintoa -terpineol. Parameters were the effect of catalyst concentration of (5%, 10% and 15%) and the reaction time (60 minutes, 120 minutes and 180 minutes). The turpentine, aquadest and isopropyl alcohol were reacted in the three neck flask at the temperature of 70°C.

The result of this study showed that the best condition the hydration of turpentine a -terpineol was achieved at 15% catalyst concentration and the reaction time of 180 minutes. The conversion was obtained to be 4.875%. K e y w o r d s — Tur p e n t i n e , Hydration, Alpha terpeneol, Catalys,Natural Zeolite. I. INTRODUCTION urpentine from Indonesia contains 65- 8% -pinene, 1% camphene, 1- 3β -pinene, 10-18% 3-carene and 1-3% line he o mpntpne a -pinene. - terpeneol. Alpha terpeneol can be used as perfume, anti- insect, anti-fungal, and disinfectant. The reaction between -pinene -terpineol is as follows $C_{10}H_{16} + H_2O \rightarrow C_{10}H_{18}O$ The - -pinene with the catalyst has been studied by several researchers. Arias et.al.

(2000) studied the hydration of turpentine -terpineol using a dealumination - terpeneol with the highest selectivity was 44% at 70% conversion. Nuritasari (2013) has -pinene -terpineol production by using natural zeolite catalysts. The TCA-ZA catalyst which has been used was washed with aquadest and reused with 15.36% reaction result. Amilia et. al (2013) has done the research the effect of Amilia et. al (2013) has done the research the effect of Manuscript received June 20, 2015. 1Chemical Engineering Departement, Universitas Lampung, 35145 Lampung, Indonesia (corresponding author to provide phone: +6281354083620; e-mail:herti.utami@ eng.unila.ac.id).

temperature on the hydration reaction of -pinene - terpeneol with natural zeolite catalyst and the best result was obtained at the temperature of 70oC and the conversion was 68.53%. -pinene hydration reaction during this homogeneous catalyst were chloroacetic acid, oxalic acid and trichloroacetic acid (TCA). Utami (2010) studied the hydration of -terpineol from turpentine using chloroacetic acid as catalyst. The bes -terpineol conversion was 54.13% at the temperature of 80°C and the reaction time was 240 minutes. Daryono (2015) who has - -terpineol by using sulfuric -terpineol conversion of 57.05% and the yield of 67.79% at temperature of 70oC.

In fact, the use of the homogeneous catalyst is corrosive and thisis not environmental friendly, so it is necessary to use a more environmental friendly catalyst. One alternative catalyst that can be used is a heterogeneous catalyst such as natural zeolite. That is more economical, easy to obtain, and environmental friendly. This research was conducted for the shesioa -terpineol from turpentine oil by using heterogeneous solid catalyst, natural zeolite, especially natural zeolite of Lampung. II.MATERIALS AND METHODS A.Chemical Turpentine obtained from Perhutani Semarang. Isopropyl, dichloromethane, HCl, Na₂CO₃, and Na₂SO₄ B.Catalyst The catalyst used was natural zeolite of Lampung which has been activated. The natural zeolite of Lampung obtained by CV.

Minatama. C. Procedure Procedure of this research includes the initial treatment of natural zeolite.That was activated with physical and chemical treatment. In the preparation step, the natural zeolite of Lampung was sieved with a size of 100 mesh, then washed with aquadest that aim to dissolve the dirt T INSIST Vol. 2 No. 2, April 2018 (89 – 92) <http://insist.unila.ac.id/> DOI:10.23960/ ins. v2i2. 8 7 Received: 02/06/2017 Accepted: 10/08/2017 Published online: 20/10/2017 INSIST Vol. 2 No. 2, October 2017 (89 - 92) 90 on the zeolite surface. Then the zeolite was dried in an oven with the temperature of 200oC for 2 hours.

After the zeolite preparation completed, the natural zeolite of Lampung as many of 300 grams was soaked with HCl 4 M solution of 1 L. Then the natural zeolite of Lampung

after dissolved with HCl was washed with aquadest to remove Cl^- ions until the pH becomes neutral. After that the zeolite was dried in an oven with the temperature of 110°C for 3 hours. Then natural zeolite of Lampung calcined in a furnace with the temperature of 400°C for 3 hours. Zeolite can already be used as a catalyst.

The natural zeolite of Lampung before activation, after activation and after reaction was analyzed with Branaeur Emmet Telle (BET), Fourier Transform Infrared (FTIR) and X-ray Flourensence (XRF) to know the content of Si/Al, surface area and the acid sites at Lampung natural zeolite. The hydration reaction was carried out in a three-neck flask that filled 20 mL of turpentine, 109 mL of aquadest, and 80 mL of isopropyl alcohol. The three- neck flask was equipped with a thermometer and a magnetic stirrer. The mixture was warmed up to the temperature of 70°C . After the temperature was reached, the natural zeolite of Lampung was loaded into the flask. The mixture was stirred and the reaction time was started to be calculated.

A sample was taken at every reaction time of 60 minutes, 120 minutes and 180 minutes at each concentration of natural zeolite of Lampung 5%, 10% and 15%. The product of the turpentine hydration reaction was introduced into the centrifuge for 15 minutes at a rotation speed of 350 rpm. The sample of centrifuge results was filtered and the natural zeolite of Lampung was not included in the product. The neutral step, the product was poured into a separating funnel to separate the top layer (product) and the bottom layer (reactants). The product has been separated, then washed with aquadest in a separation funnel.

The washed product was added 10% Na_2CO_3 solution until the pH becomes neutral. Furthermore, the product was added 1 drop of dichloromethane solution in separating funnel. The latter process was added anhydrous Na_2SO_4 to bind the residual water and the product was filtered to separate the precipitate. The -terpineol synthesis were analyzed by Gas Chromatografy (GC) and the best result was analyzed by Gas Chromatografy Mass Spectrometry (GC-MS). III.

ANALYSIS OF RESULTS Zeolite may be used as a catalyst or as a catalyst support if it has a high Si/Al content, contains acid (H^+) and absence of impurities in the pores of the zeolite that the surface area of the pore was large. To know the content of Si/Al, the surface area and the acid sites in natural zeolite of Lampung can be analyzed with Branaeur Emmet Telle (BET), Fourier Transform Infrared (FTIR) and X-ray Flourensence (XRF). The natural zeolite of Lampung has been activated by chemical and physical treatment then it was analyzed by using BET. The surface area was $35.2564 \text{ m}^2/\text{g}$. Fig 1.

The results analysis FT-IR ZAL In the Figure 1 shows the characterization results of the

natural zeolite of Lampung before activation (a) and after activation (b) and after being used as a catalyst in the -terpineol (c). The wave length indicates several peaks indicating the presence of some functional groups in the natural zeolite. Based on Figure 1. we can see the absorption of waves in zeolite (a) 787.78cm⁻¹, (b) 788.08cm⁻¹ and (c) 788.79cm⁻¹ which it shows the interpretation of bond absorption on the main structural unit of zeolite in the form Si-O. And then comes the absorption band of Si-O-Si vibration that is (a) 1018 cm⁻¹, (b) 1031 cm⁻¹ and (c) 1023 cm⁻¹. In Fig. 1.

the wave numbers (a) 3615 cm⁻¹, (b) 3635.68 cm⁻¹ and (c) 3618 cm⁻¹ show the vibration of the Si-OH group (hydroxyl group). 500 1000 1500 2000 2500 3000 3500 4000 % Transmittansi Numbers of waves (cm⁻¹) (a) (b) (c) INSIST Vol. 2 No. 2, April 2018 (89 – 92) <http://insist.unila.ac.id/> DOI:10.23960/ ins. v2i2. 8 7 Received: 02/06/2017 Accepted: 10/08/2017 Published online: 20/10/2017 INSIST Vol. 2 No. 2, October 2017 (89 - 92) 91 Furthermore the absorption bands at wave numbers (a) 1632.93cm⁻¹, (b) 1634.01cm⁻¹ and (c) 1644.00 cm⁻¹ indicate the presence of H-O-H groups.

Then the formation occurs in zeolites (b) and (c) 2146 cm⁻¹, where absorption at 2100-2400 cm⁻¹ shows the uptake of Si-H (Socrates, 1994). The Si-H absorption band appears due to the activation of the zeolite with the addition of acid and Si appears to bind H. The natural zeolite of Lampung was characterized by using XRF to analyze the elements in the mineral or rock presented in Table 1. Table 1.

The result XRF natural zeolite of Lampung Component Concentration (%) before activation After activation Al 13,636 13,033 Si 75,598 79,746 Based on the results of XRF analysis shown in Table 1, it can be seen that there was an increase of Si content in zeolite after activation, where before the activation of Si content in natural zeolite of Lampung was 75.598% and after activation at zeolite become 79.746%. In addition to the increase in Si content, in zeolites also decreases Al levels in zeolites from 13.636% before activation to 13.033% after activation.

This indicates that the activation process at natural zeolite of Lampung using HCl with 4 M concentration was successful. Activation of zeolite with HCl addition aims for dealumination (release of Al from zeolite), and the dealumination can increase the Si/Al ratio in zeolite. This is evidenced from the results of XRF in Table 1, where the ratio of Si/Al in natural zeolite after activation is higher than natural zeolite that has not been activated. In the unactivated natural zeolite has a Si/Al value of 5.544, while the Si/Al value in the activated zeolite is 6.11. The higher the Si/Al value, the higher the acidity or the more acid sites in the zeolite. The increase of acid sites it will increase the activity of zeolite.

According to Triantafillidis (2000) the more Al content in zeolites (Si/ Al ratio decreases) will cause the strength or total of zeolite acid sites to decrease. Fig 2 tof onenttiof atlys onversi - pinene - terpeneol In Figure 2. it can be seen that at a zeolite concentration of 5% there was an insignificant increase of a -terpeneol conversion from 60 min to 180 min, obtained by conversion of a -pinene to the highest a -terpeneol 0.7875% at reaction time of 180 min. At the 10% zeolite concentration increased conversion from 60 minutes to 180 minutes, where the highest conversion obtained at 180 minutes and the conversion was 3.3125%.

While at the concentration of 15% there was also a significant conversion increase from 60 minutes to 180 minutes with the highest conversion obtained at 180 minutes and the conversion was 4.875%. Based on the results of conversion, the concentration of catalyst natural zeolite of Lampung influences the conversion -pinene to -terpeneol. As the number of catalysts or concentrations of zeolite catalysts used for turpentine hydration, the higher -terpeneol conversion was obtained. The large number of catalysts affects the surface area of the catalyst during reaction.

The more catalysts used, the more active sites will be utilized during the turpentine hydration reaction. The more active sites on the zeolite then the resulting product will increase. Although in this study there is an increase in conversions, the minor conversion was obtained. This is because the natural zeolite catalyst used has a Si/Al value that is not too different from before activation so that the catalyst performance is less than optimal.

To get the optimum reaction time, then experiment again with addition of reaction time is 240 minutes at 15% catalyst concentration, as follows :

Time (minute)	Concentration ZAL 5%	Concentration ZAL 10%	Concentration ZAL 15 %
0			
1			
2			
3			
4			
5			
6			
0			
60			
120			
180			

Conversion (%)

INSIST Vol. 2 No. 2, April 2018 (89 – 92) <http://insist.unila.ac.id/>
DOI:10.23960/ ins. v2i2. 8 7 Received: 02/06/2017 Accepted: 10/08/2017 Published
online: 20/10/2017 INSIST Vol. 2 No. 2, October 2017 (89 - 92) 92 Fig - -terpeneol Based
on the Figure 3. can be seen there is the -terpeneol at 240 minutes reaction time. Where
in 60 minutes up to 180 minutes there was an increase of 4.872%, but at 240 minutes
the - terpeneol conversion decreased to 2.08%. Thus, it can be concluded at zeolite
concentration of 15% the optimal reaction time occurred at 180 min.

Analysis with mass spectrum (MS) is aimed to know the compound of hydration of -pinene for -terpeneol production. The GC-MS spectrum results are presented in Figure 4. Fig 4. The result analysis of GC-MS Based on the mass spectrum from peak 28 proves that the compound formed is -terpeneol with a molecular weight of 154 and the molecular formula C₁₀H₁₈O. IV. CONCLUSION Based on the result of the research, it

can be concluded that the natural zeolite of Lampung that has been activated has Si/Al value of 6.11 and the surface area of 35.2564 m²/g.

The synthesis of α -terpineol from turpentine using natural zeolite catalysts, it suggested that the best result was achieved at the catalyst concentration of 15% and the optimum reaction time of 180 min. The conversion of α -pinene to α -terpineol was obtained to be 4.875%. REFERENCES [1] Amilia, N., Siadi, Kusoro, dan Latifah Pengaruh Temperatur pada Reaksi Hidrasi α -pinena menjadi α -terpineol menggunakan Katalis Zeolit Alam Jurusan Kimia Fakultas Matematika dan Ilmu Pengetahuan Alam, Skripsi Jurusan Kimia Fakultas Matematika dan Ilmu Pengetahuan Alam, Universitas Negeri Semarang, 2013. [2] Arias D, Guillen Y, Hydration Using Dealuminated Faujasite as Catalysts React. Kinet. Catal. Lett., 2000, Vol. 69, No. 2., pp. 305-309. [3] Daryono, E.D.

, Siesia α -Pinene Menjadi α -Terpineol dengan Menggunakan Katalis Asam Sulfat dengan Variasi Suhu Reaksi dan Volume, Jurnal Teknik Kimia USU, 2015, Vol.4 No.2 [4] Utami, H. Buman, Sujoto, dan Sedwa, W.. " Synthesis of α -Terpineol from Turpentine by Hydration in a Batch Reactor" Proceedings 17th ASEAN Regional Symposium on Chemical Engineering, Bangkok, Thailand, November 22-23, 2010. [5] Nuritasari, A., " Pengaruh Katalis Zeolit Alam Teraktivasi dan TCA- Zeolit Alam Dalam Reaksi Hidrasi α -Pinena Menjadi α -Terpineol " Skripsi Jurusan Kimia Fakultas Matematika dan Ilmu Pengetahuan Alam Universitas Negeri Semarang, 2013. [6] Socrates, G.

, " Infrared Spectroscopy **Chicester: John Willey & Sons** Ltd., 1994. [7] Triantafillidis, C., Vlessidis, A., and Evmiridis, N., Dealuminated H- Y Zeolite: Influence of The Degree and The Type of Dealumination Method on Structural and Acidic Characteristics of H-Y Zeolite Ind. Eng. Chem, 2000, Vol. 39, No. 2, pp. 307-3019. 1 2 3 4 5 6 **60 80 100 120 140 160 180** 200 220 240 260 conversion(%) time (minute)

INTERNET SOURCES:

1% - https://www.researchgate.net/profile/Simparmin_Ginting2

1% - <http://insist.unila.ac.id/index.php/ojs/article/view/87>

<1% - <https://publications.waset.org/vol/104>

<1% -

https://ejournal.undip.ac.id/index.php/index/oai?verb=ListRecords&metadataPrefix=oai_dc&set=reaktor:RA

1% -

https://www.researchgate.net/profile/Herti_Utami/publication/280939985_Synthesis_of_alpha-Terpineol_from_Turpentine_by_Hydration_in_a_Batch_Reactor/links/55cd4d9d08aebbb8f578015/Synthesis-of-Terpineol-from-Turpentine-by-Hydration-in-a-Batch-Reactor.pdf

<1% -

https://www.researchgate.net/publication/231181915_Zeolite_Surface_As_a_Catalyst_Support_Material_for_Synthesis_of_Single-Walled_Carbon_Nanotubes

<1% -

https://www.researchgate.net/publication/311568972_Influence_of_crystal_size_on_the_catalytic_performance_of_H-ZSM-5_and_ZnH-ZSM-5_in_the_conversion_of_methanol_to_aromatics

<1% -

https://www.researchgate.net/publication/307440794_Effect_of_the_SiAl_ratio_on_the_performance_of_hierarchical_ZSM-5_zeolites_for_methanol_aromatization

1% - <https://iopscience.iop.org/article/10.1088/1757-899X/349/1/012045>

<1% -

<https://www.coursehero.com/file/p618umm/1-2-20-40-60-80-100-120-140-160-180-Frequency-4456044-7384678-0603417-5931679/>