


INFLUENCE OF GAMBIER EXTRACT MODIFICATION AS INHIBITOR OF CALCIUM SULFATE SCALE FORMATION

By Suharso Suharso



7

Influence of gambier extract modification as inhibitor of calcium sulfate scale formation

Suharso^{a,*}, Buhani^a, Hiasinta Rini Utari^a, Tugiyono^b, Heri Satria^a

^aDepartment of Chemistry, Faculty of Mathematics and Natural Sciences, University of Lampung, Jl. Soemantri Brojonegoro No. 1, Bandar Lampung, Indonesia, 35145, Tel. +62721704625; Fax: +62721702767; emails: suharso@fnipa.unila.ac.id/
suharso_s@yahoo.com (Suharso)

^bDepartment of Biology, Faculty of Mathematics and Natural Sciences, University of Lampung, Jl. Soemantri Brojonegoro No. 1, Bandar Lampung, Indonesia, 35145

Received 19 February 2019; Accepted 5 July 2019

6

ABSTRACT

Scale formation is a serious problem in many industries, especially in oil and gas industries. Therefore, in order to control the problems, this research studied the effect of the addition of gambier extract modified with kemenyan extract on the growth of calcium sulfate (CaSO_4) scale formation as a green inhibitor. The crystallization experiments were carried out by using unseeded experiment method at temperature of 90°C . The CaSO_4 crystals obtained with and without the addition of inhibitor were analyzed by scanning electron microscopy (SEM), particle size analyzer (PSA), and X-ray diffraction (XRD). The results of this experiment show that the addition of the combination of gambier and kemenyan extract with ratio of 5:9 can inhibit the growth of CaSO_4 crystals with the inhibition effectivity of 39.88%. These results were supported from the SEM and PSA data showing that the crystal size and particle size distribution of the CaSO_4 in the addition of the inhibitor are smaller than without the addition of inhibitor. In addition, analysis using XRD showed that CaSO_4 crystals undergo a change in crystalline phase with the addition of inhibitors.

Keywords: CaSO_4 ; Green inhibitor; Scaling; Gambier extract, Kemenyan extract

1. Introduction

In cooling water system, calcium sulfate (CaSO_4) often found as mineral deposits which is a problem for industries. The mineral deposits not only lowers heat exchanger performance by increasing resistance to heat transfer but also wastes energy due to increased pumping power, causing enormous economic losses [1–7]. In order to control these deposits, a number of chemical compounds have been studied to obtain an effective inhibitor to inhibit scale formation [8–11].

The use of biomass from agricultural and plantation products is not only applied as an adsorbent [12–15] but can also be used as a corrosion and scaling inhibitor [16,17].

The gambier (*Uncaria gambier* Roxb leaves) and kemenyan (*Styrax benzoin* Dryand) extracts have been reported as green inhibitor of calcium carbonate (CaCO_3) [18,19]. The modification of the gambier extract with the addition of citric and benzoic acid has been also studied in inhibiting scale formation of calcium carbonate [20]. The role of citric and benzoic acid added in the mixtures was to maintain quality of gambier extract from chemical damage.

In this research, it was studied the modification of gambier and kemenyan extracts as green inhibitor to control the scale formation of calcium sulfate (CaSO_4) with various concentrations of gambier and kemenyan extracts. The kemenyan extract from Sumatra benzoin tree used in this experiment has main chemical compounds such as benzoic

* Corresponding author.

and cinnamic acid that can replace citric and benzoic acid to maintain the quality of the mixtures. The use of the kemenyan aims to reduce production costs of the inhibitor mixtures.

2. Experimental procedure

2.1. Materials and instrumentation

The instrument used in this experiment consisted of analytical balance (Kenr & Sohn GMBH ABT 220-4M, Germany), oven (Thermo Fisher Scientific, United Kingdom), water bath (Haake S21, Thermo Fisher Scientific, USA), plastic bottle, magnetic stirrer, chemical glass, Fourier transform infrared (FTIR) spectrophotometer (Shimadzu FTIR-8400, Japan), scanning electron microscopy (SEM) (JSM 6360 LA, JEOL, Japan), particle size analyzer (PSA) (the Beckman Coulter LS 13 320 MW, manufactured in USA), and X-ray diffraction (XRD, Philip Analytical, manufactured in Netherlands).

CaCl₂ anhydrous, CH₃CH₂OH, CH₃OH, acetone, and Na₂SO₄ were ordered from commercial product of Merck, Germany. The gambier and kemenyan extract were prepared with the raw materials obtained from local market in Bandar Lampung, Indonesia.

2.2. Preparation of gambier and kemenyan extract

The gambier extract was made by pounding gambier until smooth, so that it can be used to obtain gambier powder. A total of 10 g of the gambier powder was dissolved in water to a volume of 1 L. The solution was stirred using a magnetic stirrer for 3 h at a temperature of 90°C and then the solution was filtered using filter paper. The filtered solution was a gambier extract stock solution with a concentration of 10,000 ppm. The same procedure was carried out to make kemenyan extract with a concentration of 10,000 ppm [18,19].

2.3. Testing the use of a mixture of gambier and kemenyan extract as an inhibitor of CaSO₄ crystal formation with the unseeded experiment method

2.3.1. Without the addition of inhibitors

The growth solution of 0.05 M CaSO₄ was made from mixing a solution of 0.100 M CaCl₂ and 0.100 M Na₂SO₄ each in 200 mL of distilled water at a temperature of 90°C, the mixture was stirred using a magnetic stirrer for 15 min and it was divided into eight plastic bottles of each 50 mL. The plastic bottles containing the solution were placed into the water bath at temperature of 90°C. Observations were carried out for 2 h, and every 15 min one bottle was taken to weigh the crystals formed by filtering the solution in the bottle using filter paper, washing with distilled water, and drying using an oven at 105°C for 3 h. The precipitate formed was weighed, then analyzed using a SEM instrument, PSA, and XRD.

2.3.2. With the addition of inhibitors

The inhibitor solution was made by mixing 200 mL gambier extract with 200 mL of kemenyan extract with a varied concentration ratio. The combinations of gambier and kemenyan extract were tested for its effectiveness by varying

the concentration of the mixture of gambier and kemenyan extract in which the concentration of gambier extract was made fixed. Comparison of the concentration of mixture of gambier and kemenyan extracts can be seen in Table 1. The mixture solution of gambier and kemenyan extract was stirred using a magnetic stirrer for 15 min at a temperature of 90°C, cooled and then stored in a dark bottle. Each mixture was tested for its effectiveness in inhibiting the scale formation of CaSO₄ in a growth solution of 0.05 M CaSO₄.

The growth solution of 0.05 M CaSO₄ was made by mixing each 200 mL solution of 0.100 M CaCl₂ and 0.100 M Na₂SO₄ which has been added by the inhibitor of a mixture of gambier and kemenyan extracts with a concentration comparison of 5:1. The mixture was stirred by magnetic stirrer for 15 min at temperature of 90°C and it was separated into eight plastic bottles and kept in the water bath at the same temperature. Every 15 min one bottle was taken to weigh the crystals formed by filtering the solution in the bottle using filter paper, washing it with distilled water, and drying it using an oven at 105°C for 3 h. These experiments were repeated with the mixture of gambier and kemenyan extract with the concentration ratio of 5:3, 5:5, 5:7, and 5:9. The precipitate formed was weighed; then the most effective was selected to be analyzed using instruments of SEM, PSA, and XRD.

2.4. Data analysis

To find out the effectiveness of inhibitors in inhibiting the scale formation of CaSO₄ Eq. (1) [21] given as follows can be used:

$$\text{Effectiveness of inhibitors (\%)} = 100 \times \frac{(Ca - Cb)}{(Cc - Cb)} \quad (1)$$

where Ca = CaSO₄ concentration after added inhibitor at equilibrium (g/L); Cb = CaSO₄ concentration without inhibitor at equilibrium (g/L); Cc = initial CaSO₄ concentration (g/L).

3. Results and discussion

3.1. Characterization of inhibitor extracts using FTIR spectrophotometer

Analysis using FTIR spectrophotometer served to determine the functional groups contained in the gambier and kemenyan extracts. The IR spectrum obtained for the

Table 1
Concentration comparisons of gambier (G) and kemenyan (K) extract mixtures

No.	Comparison G:K	Concentration (ppm)	
		G	K
1	5:1	250	50
2	5:3	250	150
3	5:5	250	250
4	5:7	250	350
5	5:9	250	450

gambier, kemenyan, and gambier–kemenyan extracts is presented in Fig. 1. From Fig. 1c, the emergence of a number of absorption bands related to functional groups that are owned by organic components in the gambier extract can be observed. The presence of hydroxyl (–OH) groups can be observed with the appearance of absorption bands in the area of 3,417.86–3,363.86 1/cm with a very wide intensity. The hydroxyl (–OH) absorption band in Fig. 1c appears at 3,385.07 1/cm; this corresponds to the main component of the gambier extract such as tannic acid (tannins) which is very rich in hydroxyl groups. The absorption band at wave number 2,933.3 1/cm shows the presence of aromatic C–H functional groups derived from the chemical content in the gambier extract, such as tannins. The wave number 1,627.92 1/cm shows the presence of carbonyl (C=O stretch) functional groups found in catechins (catechin anhydride) from the gambier extract. The presence of C=C groups on aromatic compounds is seen by the appearance of peaks at wave numbers 1,467.83 and 1,523.76 1/cm.

In Fig. 1b it can be observed the emergence of a number of absorption bands related to functional groups possessed by organic components in extracts of the kemenyan. In Fig. 1b strong width uptake at 3,367.1 1/cm shows the 21 H group. Uptake in 1,691.57 1/cm is characteristic of the carbonyl group (C=O) from the carboxylic acid. Group of (–C=C–) in aromatic compounds are seen by the appearance of peaks at wave numbers 1,514.12 to 1,450.47 1/cm with sharp and strong intensity. Based on the reference data, the carbonyl group in benzoic acid appears at wave numbers 1,600, O–H at 3,200–2,400, –C=C– aromatic at 1,500–1,410 and C–H (monosubstituted benzene) at 680–600 1/cm. Whereas in cinnamic acid, the carbonyl group appears at wave number 1,691.57, O–H at 3,367.71, –C=C– aromatic at 1,633.71 1/cm.

In this study, the inhibitor used was a mixture of gambier and kemenyan extract so that the extract mixture was also analyzed using an FTIR spectrophotometer as shown in




Fig. 1. IR spectrum of (a) gambier–kemenyan (5:9), (b) kemenyan, and (c) gambier extracts.

Fig. 1a. Based on the FTIR analysis, there is a slight shift in absorption such as the hydroxyl (–OH) absorption band seen at wave number 3,388.93 1/cm, the functional group of carbonyl (C=O stretch) seen at wave number 1,624.06 1/cm, the functional group of –C=C– aromatic seen at wave number 1,517.98 and 1,462.04 1/cm. These results are consistent with IR spectrum of kemenyan and gambier resulted from previous researches [19,22]. The characterization results show that in a mixture of gambier and kemenyan extracts, there are several chemical compounds that have active functional groups that can be used as inhibitors of CaSO_4 scaling.

3.2. Testing of inhibitor mixtures in inhibiting CaSO_4 scale formation

The observation of the effect of the use of a mixture of gambier (G) and kemenyan (K) extract as an inhibitor of CaSO_4 scale formation at the concentration of 0.05 M with and without inhibitors of the gambier and kemenyan extract mixtures is shown in Fig. 2.

Based on observational data obtained in Fig. 2, calculations can be performed using Eq. (1) to obtain the effectiveness of inhibitors of the mixture of the gambier and kemenyan extract as shown in Table 2.

The data obtained in Table 2 show that a mixture of gambier and kemenyan extract in a growth solution of 0.05 M CaSO_4 was able to inhibit the growth rate of CaSO_4 crystals. The addition of the inhibitors of the mixture of gambier and kemenyan extracts with a concentration ratio of 5:9 had the greatest effectiveness of 39.88%.

The crystal morphology of CaSO_4 was observed by SEM analysis, and the results can be seen in Fig. 3. Based on the results of SEM analysis in Fig. 3, it can be observed that there was a change in the size of CaSO_4 crystals in the unseeded experiment method using inhibitors of the gambier and kemenyan extract mixtures with a ratio of 5:9 at a magnification of 1,000 \times . From the results of surface morphology analysis, it can be seen that CaSO_4 crystals without inhibitors have a larger and longer size compared with CaSO_4 crystals which have been added with inhibitors of gambier




Fig. 2. Precipitation mass change of CaSO_4 at the concentration of growth solution of 0.05 M vs. time without and with the addition of inhibitor at various concentrations.

Table 2
Effectiveness of inhibitor (%) at the concentration of growth solution of 0.05 M with the various concentration of inhibitor added

Ratio of concentration (G:K) (ppm)	Effectiveness of Inhibitor (%)
5:1	17.35
5:3	22.98
5:5	24.23
5:7	31.48
5:9	39.88

and kemenyan extract mixtures which are smaller and shorter in size. Thus it can be stated that the addition of inhibitors causes changes in the size of CaSO_4 crystals and inhibitors also can change in the morphology of CaSO_4 crystals. The morphology of CaSO_4 crystal in the absence of inhibitors was larger needle-like gypsum crystals. While the morphology of CaSO_4 crystal in the presence of inhibitors was dominated by bassanite phase. The addition of the inhibitors in the growth solution of CaSO_4 causes a change the crystalline phase of most CaSO_4 crystal from the gypsum ($\text{CaSO}_4 \times 2\text{H}_2\text{O}$) to the bassanite ($\text{CaSO}_4 \times 0.5\text{H}_2\text{O}$) phase (Fig. 3).

In order to support the data obtained through SEM images, the calcium sulfate crystals obtained with and without the addition of inhibitors were characterized using powder XRD. The XRD pattern of the calcium sulfate analyzed is displayed in Fig. 4. The XRD pattern obtained shows that the data resulted by XRD support the SEM data as seen in Fig. 3. The results of the analysis using XRD showed that with the addition of inhibitors, the presence of bassanite (B) dominated the crystalline phase of calcium sulfate compared with gypsum (G). Addition of inhibitors also to the calcium sulfate growth solution presents an anhydrous anhydrite (CaSO_4) crystal phase (A) as shown

in Fig. 4. The gypsum phase is a type of hard scale phase. This phase is a crystalline phase that is difficult to clean. Whereas the bassanite and anhydrite phases are crystalline phases which are easier to clean (soft scale).

The results of this analysis also prove that the addition of inhibitors can slow the formation of CaSO_4 crystal nuclei. Addition of inhibitors can reduce the size of CaSO_4 crystals rather than without the addition of inhibitors. Smaller crystal sizes indicate that inhibitors work to reduce the formation of CaSO_4 crystals.

Crystal size changes that occur in CaSO_4 crystals without inhibitors and with inhibitors are due to the role of inhibitors which inhibit the surface of CaSO_4 crystals through adsorption on the surface of the crystal or crystal nucleus. Thus, the inhibition mechanism that occurs is thought to be through the inhibitor adsorption of a mixture of the gambier and kemenyan extract to the surface of CaSO_4 crystals so that the crystal nucleus as a new growth unit derived from growth solution is blocked by inhibitors of the gambier and kemenyan extract and it cannot attach to the active growth site on the crystal surface CaSO_4 for growth. The inhibition of growth units by inhibitors causes the growth rate of CaSO_4 scale to slow down. The inhibition of CaSO_4 crystal growth will result in changes in crystal size of CaSO_4 . This is in line with the research of Sikirić and Milhofer, who examined the effect of organic molecules on the crystallization of biomineral in solutions that showed changes in the growth rate and scale morphology of biomineral crystals due to the addition of organic molecules with certain functional groups [23].

To further prove changes in the size of CaSO_4 crystals without and with the addition of G:K inhibitors, an analysis using a particle size analyzer (PSA) was performed on CaSO_4 crystals obtained as seen in Fig. 5. Particle size distribution of CaSO_4 with the addition of G:K inhibitors comes smaller than without the addition of inhibitors as shown in Fig. 5. In the graph without the addition of inhibitors (Fig. 5), it is known that the CaSO_4 crystal size diameter has a mean and median of 118.8 and 119.6 nm, respectively. After the




Fig. 3. Morphology of CaSO_4 crystals (a) without inhibitors and (b) with inhibitors of the mixture of gambier and kemenyan extracts with a ratio of 5:9 at magnification of 1,000 \times .




Fig. 4. XRD patterns of the calcium sulfate in the absence and presence of inhibitor mixtures (G:K = 5:9).

addition of a mixed inhibitor of GK (5:9), the CaSO_4 crystal size diameter has a mean and median of 83.9 and 82.1 nm, respectively.

Inhibitor can affect the nucleation and growth of CaSO_4 crystals, for example, by forming complexes or chelating agents with the active ions in growth solution of CaSO_4 . Inhibitor can also affect the nucleation and growth of CaSO_4 crystals by adsorbing to active crystal sites and inhibiting nucleation or crystal growth of CaSO_4 . In the case of this experiment, the use of gambier and kemenyan extract mixture as inhibitor of CaSO_4 crystal allows the formation of complexes with Ca^{2+} ions as well as the inhibition of the growth of calcium sulfate crystals through adsorption on the CaSO_4 crystal surface. This is caused by the presence of chemical compounds such as tannic acid, catechin, quercetin, p-coumaryl cinnamate, cinnamic acid, p-coumaryl benzoate, isovanillin and benzoic acid which are contained in the gambier and kemenyan extract which




Fig. 5. Particle size distribution of CaSO_4 crystals with and without inhibitor of G:K (5:9) at the concentration of CaSO_4 growth solution of 0.05 M.

have active groups as carboxylate and ketone group that can bind to Ca^{2+} ions. The presence of tannic acid, catechin, and quercetin as an organic molecule rich in $-\text{OH}$ groups can adsorb onto the surface of CaSO_4 crystals, change the crystal morphology of CaSO_4 , and finally inhibit the growth rate of CaSO_4 crystal. Similar results were also found in the addition of inhibitors of organic molecules causing a slow-down in the growth of CaSO_4 crystals as well as a change in the phase of CaSO_4 crystals [6,23–27]. Comparison of several inhibitors with other researchers is listed in Table 3. In general, the scale inhibition performance depends also on the concentration of growth solution and the type of inhibitor itself. Some commercial inhibitors (poly(itaconic acid-co-sodium vinylsulfonate and acrylic acid-oxalic acid-allylpolyethoxy carboxylate-8-hydroxy-1,3,6-pyrene trisulfonic acid trisodium salt (pyranine)) work very effectively at high concentrations of solution growth (Table 3). But some inhibitors such as phosphonate (P-Nate), polyacrylate, and polyaspartic acid are less effective at low concentrations of growth solutions as displayed in Table 3. In this case, the concentration of CaSO_4 growth solution is 0.05 M;

Table 3
Comparison of several inhibitors in inhibiting CaSO_4 crystal formation

Inhibitors	Growth solution concentration of Ca^{2+} (M)	Concentration of inhibitor (ppm)	Efficiency of inhibitor (%)	References
Gambier (G) and kemenyan (K) extract	0.0500	G: 250 K: 50–450	17–40	This work
Poly(itaconic acid-co-sodium vinylsulfonate)	0.3500	200–600	33–54	[27]
Acrylic acid-oxalic acid-allylpolyethoxy carboxylate-8-hydroxy-1,3,6-pyrene trisulfonic acid trisodium salt (pyranine)	0.0500–0.0750	4	87–96	[6]
Poly(acrylic acid)	0.0500	1–4	18–88	[6]
Homopolymer of polymaleic acid	0.0180	4	67	[6]
Terpolymer of polymaleic acid	0.0180	4	37	[6]
Copolymer of polymaleic acid	0.0180	4	12	[21]
Phosphonate	0.0180	4	5	[21]
Polyacrylate	0.0180	4	13	[21]
Polyepoxysuccinic acid	0.0003–0.0015	10	73–97	[28]
Polyaspartic acid	0.0150	4	25	[29]




Fig. 6. Change of gambier extract (a) without the addition of kemenyan extract and (b) with the addition of kemenyan extract after being left alone for 2 weeks.

this concentration is enough higher. If it is compared with other inhibitors in Table 3, this inhibitor is still reasonable considering that from the side of the inhibitor price, it will be much cheaper for industrial applications. It may be predicted that this inhibitor can be used effectively for the concentration of growth solution lower than 0.05 M. Unfortunately in our experiments, the use of too low concentrations was difficult to do in observing changes in the weight of the crystals formed. As it is known that the performance of inhibitor will increase when the concentration of growth solution decreases. This case was observed at the addition of acrylic acid–oxalic acid–allylpolyethoxy carboxylate–8-hydroxy-1,3,6-pyrene trisulfonic acid trisodium salt (pyranine) (AA–APEM–APTA) in inhibiting of CaSO_4 crystal growth with decreasing of the concentration of Ca^{2+} and evidently the concentration of Ca^{2+} as the growth solution of CaSO_4 crystal decreased by 50%, the inhibition effectiveness of (AA–APEM–APTA) raised by 9% [6].

3.3. Quality of the inhibitor mixtures

In addition to the inhibition of the growth of CaSO_4 crystals, the addition of kemenyan extract in gambier extract can slow down the damage of gambier extract. This can be seen in Fig. 6 which shows that the gambier extract before kemenyan extract added within 2 weeks showed the growth of fungi and impurities, while the gambier extract mixed with extract of kemenyan was clear without impurity and no fungal growth was found. The kemenyan extract can slow the growth of fungi because it contains benzoic acid and cinnamic acid which can be used as antimicrobial and antifungal. In addition, the addition of kemenyan extract in gambier extract can increase the quality of the inhibitor mixture. The kemenyan extract can be used to substitute chemical compound as benzoic and citric acid in modification of gambier extract as scaling inhibitor as previous reported [20]. The use of kemenyan extract as a mixture has its own advantages because it is relatively much cheaper than the chemical compounds of citric and benzoic acid. In addition, the use of kemenyan extract can reduce the price of inhibitors.

4. Conclusions

A mixture of the gambier and kemenyan extract acts as an inhibitor of calcium sulfate (CaSO_4) scale formation.

The gambier and kemenyan extracts in the ratio of the mixture concentration of 5:9 have good quality of an inhibitor mixtures as an inhibitor of CaSO_4 scale formation with the effectiveness of 39.88% in a growth solution of 0.05 M. The results of SEM observations showed a significant change between CaSO_4 crystal without and with the addition of mixed inhibitors of gambier and kemenyan extract. The crystal morphology of CaSO_4 with the addition of this inhibitor has a smaller and shorter size compared with the crystal morphology of CaSO_4 without the addition of inhibitors.

Acknowledgements

This study was supported by research grant from Directorate of Research and Community Service, Directorate General of Strengthening Research and Development, Ministry of Research, Technology and Higher Education (Kemenristekdikti), Republic of Indonesia with contract number 062/SP2H/LT/DRPM/2018.

References

- [1] H. Wang, M. Gao, Y. Guo, Y. Yang, R. Hu, A natural extract of tobacco rob as scale and corrosion inhibitor in artificial seawater, *Desalination*, 398 (2016) 198–207.
- [2] S.R. Popuria, C. Hall, C.C. Wang, C.Y. Chang, Development of green/biodegradable polymers for water scaling applications, *Int. Biodeterior. Biodegrad.*, 95 (2014) 225–231.
- [3] Suharso, Buhani, S.D. Yuwono, Tugiyono, Inhibition of calcium carbonate (CaCO_3) scale formation by calix[4] resorcinarene compounds, *Desal. Wat. Treat.*, 68 (2017) 32–39.
- [4] M.K. Jensen, M.A. Kelland, A new class of hyperbranched polymeric scale inhibitors, *J. Pet. Sci. Eng.*, 94–95 (2012) 66–72.
- [5] Suharso, Buhani, T. Suhartati, The role of C-methyl-4,10,16,22-tetramethoxy calix[4] arene as inhibitor of calcium carbonate (CaCO_3) scale formation, *Indo. J. Chem.*, 9 (2009) 206–210.
- [6] H. Wang, Y. Zhou, Q. Yao, W. Sun, Calcium sulfate precipitation studies with fluorescent tagged scale inhibitor for cooling water systems, *Polym. Bull.*, 72 (2015) 2171–2188.
- [7] Suharso, Buhani, L. Aprilia, Influence of calix[4]arene derived compound on calcium sulphate scale formation, *Asian J. Chem.*, 26 (2014) 6155–6158.
- [8] E. Badens, S. Veessler, R. Boistelle, Crystallization of gypsum from hemihydrate in presence of additives, *J. Cryst. Growth*, 198 (1999) 704–709.
- [9] S. Titiz-Sargut, P. Sayan, B. Avci, Influence of citric acid on calcium sulfate dihydrate crystallization in aqueous media, *Cryst. Res. Technol.*, 42 (2007) 119–126.
- [10] S.B. Ahmed, M.M. Tlili, M.B. Amor, Influence of a polyacrylate antiscalant on gypsum nucleation and growth, *Cryst. Res. Technol.*, 43 (2008) 935–942.
- [11] Ö. Doğan, E. Akyol, M. Öner, Polyelectrolytes inhibition effect on crystallization of gypsum, *Cryst. Res. Technol.*, 39 (2004) 1108–1114.
- [12] S. Dardouri, J. Sghaier, A comparative study of adsorption and regeneration with different agricultural wastes as adsorbents for the removal of methylene blue from aqueous solution, *Chin. J. Chem. Eng.*, 25 (2017) 1282–1287.
- [13] Suharso, Buhani, Biosorption of Pb(II), Cu(II) and Cd(II) from aqueous solution using cassava peel waste biomass, *Asian J. Chem.*, 23 (2011) 1112–1116.
- [14] C.E. Flores-Chaparro, L.F.C. Ruiz, M.C.A. de la Torre, M.A. Huerta-Diaz, J.R. Rangel-Mendez, Biosorption removal of benzene and toluene by three dried macro algae at different ionic strength and temperatures: algae biochemical composition and kinetics, *J. Environ. Manage.*, 193 (2017) 126–135.
- [15] Buhani, Suharso, Z. Sembiring, Immobilization of *Chetoceros* sp. microalgae with silica gel through encapsulation technique as

- adsorbent of Pb metal from solution, *Orient. J. Chem.*, 28 (2012) 271–278.
- [16] S. Jyothi, K. Rathidevi, D. Jalajaa, P.S. Ratnakumar, Inhibitive effect of *Mussaenda frondosa* leaves extract on mild steel corrosion-statistical and theoretical view, *Rasayan J. Chem.*, 12 (2019) 272–277.
- [17] M.K. Nayunigari, A. Maity, S. Agarwal, V.K. Gupta, Curcumin-malic acid based green copolymers for control of scale and microbiological growth applications in industrial cooling water treatment, *J. Mol. Liq.*, 214 (2016) 400–410.
- [18] Suharso, Buhani, S. Bahri, T. Endaryanto, Gambier extracts as an inhibitor of calcium carbonate (CaCO_3) scale formation, *Desalination*, 265 (2011) 102–106.
- [19] Suharso, N.A. Sabriani, Tugiyono, Buhani, T. Endaryanto, Kemenyan (*Styrax benzoin* Dryand) extract as green inhibitor of calcium carbonate (CaCO_3) crystallization, *Desal. Wat. Treat.*, 92 (2017) 38–45.
- [20] Suharso, T. Reno, T. Endaryanto, Buhani, Modification of gambier extracts as green inhibitor of calcium carbonate (CaCO_3) scale formation, *J. Water Process Eng.*, 18 (2017) 1–6.
- [21] S. Patel, M.A. Finan, New antifoulants for deposit control in MSF and MED plants, *Desalination*, 124 (1999) 63–74.
- [22] G. Yeni, K. Syamsu, O. Suparno, E. Mardiyati, H. Muchtar, Repeated extraction process of raw gambiers (*Uncaria gambier* Robx.) for the catechin production as an antioxidant, *IJAER*, 9 (2014) 24565–24578.
- [23] M.D. Sikirić, H.F. Milhofer, The influence of surface active molecules on the crystallization of biominerals in solution, *Adv. Colloid Interface Sci.*, 128–130 (2006) 135–158.
- [24] Y.W. Wang, F.C. Meldrum, Additives stabilize calcium sulfate hemihydrate (bassanite) in solution, *J. Mater. Chem.*, 22 (2012) 22055–22062.
- [25] N.B. Singh, B. Middendorf, Calcium sulphate hemihydrate hydration leading to gypsum crystallization, *Prog. Cryst. Growth Charact. Mat.*, 53 (2007) 57–77.
- [26] T. Rabizadeh, C.L. Peacock, L.G. Benning, Carboxylic acids: effective inhibitors for calcium sulfate precipitation?, *Mineral. Mag.*, 78 (2014) 1465–1472.
- [27] M.P. Alvarez, R.O. Roa, E.S. Castruita, E.B. González, R.C. Dévora, D.N. Alvarez, M.P. Jiménez, L.S.Z. Rivera, Growth inhibition in calcium sulfate crystal using a copolymer in oil fields: theoretical study and experimental evaluations, *Iran. Polym. J.*, 27 (2018) 927–937.
- [28] Y. Sun, W. Xiang, Y. Wang, Study on polyepoxysuccinic acid reverse osmosis scale inhibitor, *J. Environ. Sci.*, 21 (2009) S73–S75.
- [29] D. Liu, W. Dong, F. Li, F. Hui, J. Ledion, Comparative performance of polyepoxysuccinic acid and polyaspartic acid on scaling inhibition by static and rapid controlled precipitation methods, *Desalination*, 304 (2012) 1–10.

INFLUENCE OF GAMBIER EXTRACT MODIFICATION AS INHIBITOR OF CALCIUM SULFATE SCALE FORMATION

ORIGINALITY REPORT

10%

SIMILARITY INDEX

PRIMARY SOURCES

- | | | |
|---|--|-----------------|
| 1 | www.deswater.com
Internet | 79 words — 2% |
| 2 | www.mysciencework.com
Internet | 52 words — 1% |
| 3 | lutpub.lut.fi
Internet | 26 words — 1% |
| 4 | icpam-04.naturalspublishing.com
Internet | 18 words — < 1% |
| 5 | Wang, Hongqing, Daoguang Wang, Zhibao Li, and G. P. Demopoulos. "Solubility and scale prevention of gypsum in transportation pipes of well brine with salinities up to 5 M at temperature range of 278â€"298 K", <i>Desalination and Water Treatment</i> , 2010.
Crossref | 12 words — < 1% |
| 6 | Xinhai Wang, Xiaogai Lv, Ben Zhang, Bin Xu, Ying Xu. "Scale Inhibition Performance Research of Polyaspartic Acid/Diethylenetriamine Graft Copolymer", <i>Journal of Chemical Engineering of Japan</i> , 2015
Crossref | 12 words — < 1% |
| 7 | "Contents Vol. 169", <i>DESALINATION AND WATER TREATMENT</i> , 2019
Crossref | 12 words — < 1% |
| 8 | Qing Du, Yawen Wang, Aimin Li, Hu Yang. "Scale-inhibition and flocculation dual-functionality of | 11 words — < 1% |

-
- 9 tsukuba.repo.nii.ac.jp 11 words — < 1%
Internet
-
- 10 Seo, M.. "Effect of carbon content on the microstructure and properties of (Ti⁰".⁷W⁰".³)C-Ni cermet", International Journal of Refractory Metals and Hard Materials, 201107 11 words — < 1%
Crossref
-
- 11 D. Van der Helm, W. A. Franks. " The crystal structure of bis-(-serinato)copper(II) ", Acta Crystallographica Section B Structural Crystallography and Crystal Chemistry, 1969 10 words — < 1%
Crossref
-
- 12 Nor Zakiah Nor Hashim, El Hassane Anouar, Karimah Kassim, Hamizah Mohd Zaki, Abdulrahman I. Alharthi, Zaidi Embong. "XPS and DFT investigations of corrosion inhibition of substituted benzylidene Schiff bases on mild steel in hydrochloric acid", Applied Surface Science, 2019 10 words — < 1%
Crossref
-
- 13 Shaopeng Zhang, Haojie Qu, Zhen Yang, Chang-e Fu, Ziqi Tian, Weiben Yang. "Scale inhibition performance and mechanism of sulfamic/amino acids modified polyaspartic acid against calcium sulfate", Desalination, 2017 10 words — < 1%
Crossref
-
- 14 www.tandfonline.com 10 words — < 1%
Internet
-
- 15 Kim, D.H.. "Gypsum scale reduction and collection from drainage water in solar concentration", Desalination, 20110115 9 words — < 1%
Crossref
-
- 16 S . Jyothi, K . Rathidevi, D . Jalajaa, P. S . Samuel Ratnakumar. "INHIBITIVE EFFECT OF Mussaenda 9 words — < 1%

17 Mualla Öner, Aslam Khan, Saeed R. Khan. "Importance of Calcium-Based Scales in Kidney Stone", Elsevier BV, 2015

Crossref

9 words — < 1%

18 Seyoung Kim, Jewon Choi, Misook Lee, Soo-Hyung Choi, Kookheon Char. "Inorganic Crystallization Engineered by the Dynamic Adsorption of Linear and Particulate Polyelectrolytes", Chemistry of Materials, 2018

Crossref

9 words — < 1%

19 uad.portalgaruda.org

Internet

9 words — < 1%

20 Yerzhan A. Issabayev, Galina I. Boiko, Nina P. Lyubchenko, Yerengaip M. Shaikhutdinov et al. "Synthesis of unexplored aminophosphonic acid and evaluation as scale inhibitor for industrial water applications", Journal of Water Process Engineering, 2018

Crossref

9 words — < 1%

21 docs.di.fc.ul.pt

Internet

9 words — < 1%

22 Lan Yang, Wenzhong Yang, Bin Xu, Xiaoshuang Yin, Yun Chen, Ying Liu, Yan Ji, Ying Huan. "Synthesis and scale inhibition performance of a novel environmental friendly and hydrophilic terpolymer inhibitor", Desalination, 2017

Crossref

8 words — < 1%

23 upcommons.upc.edu

Internet

8 words — < 1%

24 eprints.whiterose.ac.uk

Internet

8 words — < 1%

25 S. Titiz-Sargut. "Influence of citric acid on calcium sulfate dihydrate

crystallization in aqueous media", Crystal Research and Technology, 02/2007

Crossref

8 words — < 1 %

26 A. Sedik, D. Lerari, A. Salci, S. Athmani, K. Bachari, İ.H. Gecibesler, R. Solmaz. "Dardagan Fruit extract as eco-friendly corrosion inhibitor for mild steel in 1 M HCl: Electrochemical and surface morphological studies", Journal of the Taiwan Institute of Chemical Engineers, 2020

Crossref

8 words — < 1 %

27 etheses.whiterose.ac.uk

Internet

8 words — < 1 %

28 Antonio Colmenar-Santos, Elisabet Palomo-Torrejón, Francisco Mur-Pérez, Enrique Rosales-Asensio. "Thermal desalination potential with parabolic trough collectors and geothermal energy in the Spanish southeast", Applied Energy, 2020

Crossref

7 words — < 1 %

29 Yiyi Chen, Yuming Zhou, Qingzhao Yao, Yunyun Bu, Huchuan Wang, Wendao Wu, Wei Sun. "Evaluation of a low-phosphorus terpolymer as calcium scales inhibitor in cooling water", Desalination and Water Treatment, 2014

Crossref

6 words — < 1 %

EXCLUDE QUOTES ON
EXCLUDE BIBLIOGRAPHY ON

EXCLUDE MATCHES OFF