Febriyanti_2021_J._Phys.__Conf ._Ser._1751_012092

by Hanif Amrulloh

Submission date: 28-Jan-2021 04:50PM (UTC+0700) Submission ID: 1496149775 File name: Febriyanti_2021_J._Phys.__Conf._Ser._1751_012092.pdf (1.42M) Word count: 3975 Character count: 19797 PAPER · OPEN ACCESS

Pyrolitic conversion of palm oil into liquid fuel using protonated zeolite-X prepared from rice husk silica and aluminum foil as catalyst

5 To cite this article: T D Febriyanti et al 2021 J. Phys.: Conf. Ser. 1751 012092

View the article online for updates and enhancements.



IOP ebooks[™]

Bringing together innovative digital publishing with leading authors from the global scientific community.

Start exploring the collection-download the first chapter of every title for free.

This content was downloaded from IP address 103.3.46.247 on 28/01/2021 at 01:27

IOP Publishing

ASMI 2020 Journal of Physics: Conference Series

1751 (2021) 012092 doi:10.1088/1742-6596/1751/1/012092

Pyrolitic conversion of palm oil into liquid fuel using protonated zeolite-X prepared from rice husk silica and aluminum foil as catalyst

T D Febriyanti¹, W Simanjuntak^{2,*}, K D Pandiangan²

¹ Postgraduate Student of Chemistry Department, University of Lampung, Jl. Sumantri Brodjonegoro no 1, Bandar Lampung 35145, Indonesia

² Department of Chemistry, Faculty of Mathematics and Natural Sciences, University of Lampung, Jl. Sumantri Brodjonegoro no 1, Bandar Lampung 35145, Indonesia

email: wasinton.simanjuntak@fmipa.unila.ac.id2,*, tikadwifebriyanti16@gmail.com1, kamisah.delilawati@fmipa.unila.ac.id2

Abstract. Zeolite-X was successfully synthesized based on silica of rice husk and aluminum foil with the variation of sodium silicate aging time of 24, 48, 72, and 96 hours with a crystallization time of 96 hours as evidenced by XRD analysis with a 20 angle peak diffractogram pattern similar to the IZA standard. Zeolite-X with sodium silicate aging time of 24 hours is the best zeolite-X with XRF analysis with components Na2O 0.436%, Al2O3 33.933%, and SiO2 65.631%, and the SEM surface morphology shape crystal was homogeneous cubes. Protonated zeolite-X or zeolite H-X has been successfully synthesized through the ion exchange process of zeolite-X with 2M NH₄NO₃ solution which had been proven by XRF analysis to reduce Na₂O from 0.436% to 0.179%. Zeolite-X and zeolite H-X have the same 20 angle diffractogram pattern. In SEM analysis, the surface morphology of zeolite H-X had a formless surface morphology. Zeolite H-X was applied in pyrolysis experiments using palm oil to produce liquid fuel. Liquid fuel was analyzed by GC-MS with components 77% hydrocarbon, 16% acid, and 7% ketones.

Keywords: zeolite-X, zeolite H-X, pyrolysis, liquid fuel.

1. Introduction

The need for fuel was increasing along with human growth. All aspects of human needs including transportation, household and industrial needs require fuel. It had resulted in the depletion of petroleum reserves which can lead to fuel scarcity, so was is necessary to anticipate using alternative fuels, one of which is liquid fuel. Liquid fuel is a renewable alternative fuel produced from organic raw materials obtained from the cracking (pyrolysis) of biomass. Liquid fuel resulting from pyrolysis was a fuel that attracts attention because its production does not require specific raw materials, meaning that it can be applied to any biomass. Biomass that has been carried out includes a mixture of used cooking oil and plastic wa226 [1], karanja seeds [2], coconut oil and palm oil [3,4], palm oil bunches and polystyrene waste [5], a mixture of rubber seed oil and sugarcane bagasse [6], neem seeds [7], and methyl ester from



Content from this work may be used under the terms of the Creative Commons Attribution 3.0 licence. Any further distribution of this work must maintain attribution to the author(s) and the title of the work, journal citation and DOI. Published under licence by IOP Publishing Ltd 1

ICASMI	2020

cooking oil [8]. In this paper using pare 12 oil used as an alternative for liquid fuel due to abundant availability of palm oil in Indonesia and Indonesia is the largest palm oil producing country in the world.

The conversion of bid 21 ss to liquid fuel can use a catalyst or without a catalyst. However, the use of catalysts can improve fuel properties such as calor 13 value and reduce fuel viscosity and increase liquid fuel yield by reducing high pyrolysis conditions (350-450 °C, 5-15 MPa) which leads to the formation of gas and char [9-12]. This article uses a heterogeneous catalyst in the form of zeolites.

Zeolite was an important material used in various applications, one of which is applied as a catalyst used in the petrochemical and oil refining industries to separate and classify molecules according to their dimensions. In applications the adsorbent was used for the purification of air, soil and water, removing radioactive contaminants. Zeolite could be used in collecting waste heat and solar thermal energy, used for household purposes such as detergents. Increasing renewable energy and the environment also requires zeolites, such as converting biomass, fuel cells, capturing and converting CO_2 , and storing heat energy [13].

One type, zeolite-X has a pore size around 8 Å with a cubic surface morphology, and a molar propotion between SiO_2/Al_2O_3 between 11 to 3.The unit of zeolite-X forming structure consists of eight adjacent β -type spheres connected by six rings using oxygen bridges to connect to each other, forming a largest that can be accessed by a twelve-pore system with three-dimensional rings [14]. These distinctive crystal structure characteristics are advantageous for high exchange capacities, adsorption cationic and radionuclear [15].

20

In this article zeolite-X was synthesized using rice husk silica extracted by the alkaline method [6,16] as the Si source and aluminum foil as the Al source. The use of rice husk silica was profitable because rice husks were very available in nature and renewable. In addition, rice husk silica was cheaper than other types of silica that are commonly used. Use aluminum foil instead of aluminum salt as it was cheaper than aluminum salt. The resulting zeolite was calcined at temperture of 550 °C during six hours. The zeolite-X produced is known as zeolite Na-X. One of the efforts being developed was to convert zeolite Na-X into protonated zeolite-X or zeolite H-X.

Zeolite-X is used in many applications such as catalysts [17-19], gas separation in permanent gas streams [20], wastewater treatment [21], adsorption [22], biomedical [23], rapid softening of water hardness [24], and wastewater treatment [25]. The ability of zeolites as catalysts is related to the active availability centers in the channels between zeolites. These active centers are formed to the presence of both Brønsted and Lewis-type acid functional groups [13]. Many modification strategies are used to improve the performance of the acid sites or active centers on zeolite-X, one of which is the ion-exchange process [25] In this method Na⁺ is placed with H⁺ ions.

19

In this study, zeolite H-X was synthesized from zeolite-X using rice husk silica and aluminum foil in two stages. The first stage was synthesizing zeolite-X then ion-exchange process using 2M NH₄NO₃ solution [26] which was then recalculated at 550 °C for six hours to get the zeolite H-X. Zeolite H-X was applied to the pyrolysis method to produce liquid fuel.

2. Meterials and methods

2.1. Materials

The materials used in this study included rice husks from rice mills Way Lima, Pesawaran, HNO₃ solution from Aldrich, NaOH pellets and NH_4NO_3 from Merck, aquadest, universal indicators, filter paper, and aluminum foil.

Journal of Physics: Conference Series

IOP Publishing

2.2. Instruments

Zeolite-X and zeolite H-X were analyzed using PHILIPS-binary XRD to see the crystalline structure of the zeolite, XRF PANalytical Epsilon 3 to see the content contained in zeolites, and SEM FEI Inspeks S 50 to see the surface morphology of the zeolite. Zeolite H-X is applied to the pyrolysis method to produce liquid fuel which is then analyzed. GCMS-QP2010 SE SHIMADZU, comprehensive with the MS NIST17.LIB Library System is used for the analysis and chemical compounds of the resulting liquid fuel.

6

2.3.Synthesis of zeolite-X

Zeolite-X was synthesized using a hydrot 24 mal method with a composition ratio of $4Na_2O$: Al_2O_3 : 4.8SiO₂: 120H₂O prepared from a mixture of sodium silicate solution and aluminum foil. The synthesis of zeolite-X was initiated by weighing 11.11 grams of NaOH pellets, 1.875 grams of aluminum foil, and 10 grams of rice husk silica using previous research [6,16]. NaOH pellets were then dissolved with 120 mL of distilled water and added to silica rice husk slowly while stirring for 3 hours in a boiling state. After all the silica has dissolved, the sodium silicate solution was filtered using filter paper to separate it from the impurities that were still present in the solution. Furthermore, the sodium silicate solution was aging for 24, 48, 72, and 96 hours. Next, the sodium silicate solution is added with aluminum foil which has been cut into small pieces by spreading it evenly and then stirring for 3 hours until a homogeneous gel is formed. In the next stage, the gel was transferred to Teflon and put into an autoclave, then aging for 24 hours in a closed state to grow zeol 7 crystal nuclei. After that, the sample was transferred to an oven to undergo the crystallization stage at 100 °C for 96 hours. After the crystallization process was complete, the sample was sloval filtered with filter paper to separate the zeolite formed from the remaining filtrate in the autoclave and washed with distilled water until it reaches pH 8. The sample was then dried in an oven at 80 °C for 24 hours. In the final stage, the dried sample was calcined at 550 °C for 6 hours to activate the zeolite.

2.4 Synthesis of zeolite H-X

Zeolite H-X was made using the ion exchange method, which was exchanging sodium metal with hydrogen metal in zeolite-X. Modification of zeolite-X to zeolite H-X by using the adsorption ion-exchange process [26] used zeolite-X which had been calcined by dissolving zeolite-X into 2M NH₄NO₃ solution for 6 hours at 15 °C with a zeolite/solution ratio of 1/10 mL to obtain zeolite NH₄⁺-X, then zeolite NH₄⁺-X results was washed using distilled water, filtered, and dried at 80 °C. The zeolite NH₄⁺-X formed was calcined at 550 °C for 6 hours to obtain zeolite H-X.

2.5 Pyrolysis experiment

Pyrolysis experiment to produce liquid fuel, the first step was to mix 250 mL of palm oil with 12.5 grams zeolite H-X catalyst and then mix well. Then the 18 ture was put into the pyrolysis reactor which had been assembled on the pyrolysis instrument, then heated to a temperature of 450 °C. The steam formed was flowed from the reactor and then cooled in the condenser to produce distillate and the liquid produced was collected. Pyrolysis was carried out for 3 hours. The liquid was transferred into separatory funnel for separation of organic phase (liquid fuel) and water phase. The liquid fuel obtained was then characterizati 17 by GCMS, with the support of MS List17.LIB Library System for tentative identification of the chemical compounds of the liquid fuel.

9

3. Results and discussion

3.1 Characterization of zeolite-X and zeolite H-X

XRD analysis was carried out to determine the compounds or crystals formed in a crystalline material so that the structure, orientation, and size of the crystals are known. The resulting XRD pattern was matched pair with the XRD pattern of IZA (International Zeolite Association). Zeolite-X had been synthesized using a different sodium silicate aging method has the same diffractogram pattern as the diffractogram pattern of IZA. This proves of zeolite-X had been successfully synthesized in Figure 1.

Journal of Physics: Conference Series





Figure 1. XRD zeolite-X diffractogram (a) aging 96 hours, (b) aging 72 hours, (c) aging 48 hours, (d) aging 24 hours, and (e) IZA.

Table 1: Comparison of 2θ and the intensity of the XRD diffractogram for zeolite-X IZA standart and zeolite-X.

Zeolit-	X IZA	Zeolit-	X (24 h)	Zeolit-	X (48 h)	Zeolit-	X (72 h)	Zeolit-	X (96 h)
20	%	20	%	20	%	20	%	20	%
6,11	100	6,12	100	6,03	80,83	5,99	58,25	5,99	34,42
9,98	10,15	10,01	20,16	9,98	46,44	9,86	48,73	9,85	50,59
15,41	6,09	15,45	25,78	15,34	71,30	15,32	69,81	15,31	76,79
23,28	6,28	23,35	45,74	23,24	100	23,20	100	23,21	100
30,91	5,84	30,37	14,27	30,90	88,99	30,87	90,00	30,88	89,22

From Table 1, it is presented that the four zeolite-X synthesized matching with the 2θ angle of the IZA standard. Zeolite-X synthesized by sodium silicate aging method did not affect the 2θ angle peak shift but did affect its intensity. Zeolite-X with the best 24 hours sodium silicate aging which best comform the peak of the 2θ angle and intensity in Figure 2. Zeolite-X was analyzed XRF containing 0.436% Na₂O, 33.933% Al₂O₃, and 65.631% SiO₂. This proves that zeolite is the main component of aluminum and silicates.



Figure 2. XRD zeolite-X diffractogram (a) aging 24 hours (b) IZA.

1751 (2021) 012092 doi:10.1088/1742-6596/1751/1/012092

IOP Publishing

Journal of Physics: Conference Series

Zeolite-X with the 24-hours aging with the ion-exchange process using 2M NH_4NO_3 solution to form zeolite H-X which was then analyzed using XRF and XRD. In XRF analysis, zeolite-X had been successfully converted into zeolite H-X as evidenced by a decrease in the Na_2O component from 0.436% to 0.179%. In the XRD analysis, there wasn 16 hange in the XRD diffractogram pattern which showed

that the ion-exchange process didn't change the crystal structure of the zeolite which was presented in Figure 3.



Figure 3. XRD diffractogram (a) zeolite H-X, (b) zeolite X.

The results of SEM morphology (Figure 4) depicts zeolite-X synthesized by 24 hours aging method homogeneous cuboid shape and size according to the literature [27]. However, the morphology of SEM zeolite H-X (Figure 4) was synthesized from zeolite-X using the ion-exchange process with 2M NH_4NO_3 solution with a different appearance from zeolite-X (Figure 5). In zeolite H-X, the structure changes to be irregular but with homogeneous shape and size.



Figure 4. The results of the SEM morphology of zeolite-X aging 24 hours with a magnification of (a) 5000x, (b) 10000x, (c) 20000x, and (d) 50000x.

IOP Publishing

ICASMI 2020 Journal of Physics: Conference Series





Figure 5. The results of the SEM morphology of zeolite H-X aging 24 hours with a magnification of (a) 5000x, (b) 10000x, (c) 20000x, and (d) 50000x.







The pyrolysis product of the biomass sample in the form of liquid fuel is reported in the literature [2-7], the liquid fuel GC-chromatogram presented in Figure 6 shows that the liquid fuel consists of many compounds, and it need help with MS NIST17.LIB Library System for identified compounds, as many as 41 temporary identified compounds were described in Table 2.

ICASMI 2020 Journal of Physics: Conference Series IOP Publishing

doi:10.1088/1742-6596/1751/1/012092

1751 (2021) 012092

Peak	Ret.	Percentage	Compound Name	Formula
No.	Time	(%)		
	(Minute)			
1.	2.881	1.04	1-Decene	$C_{10}H_{20}$
2.	2.942	2.00	Decane	$C_{10}H_{22}$
3.	3.133	0.80	Cycloheptanone	$C_7H_{12}O$
4.	3.444	1.10	n-Butylbenzene	$C_{10}H_{14}$
5.	3.656	1.95	1-Undecene	$C_{11}H_{22}$
6.	3.770	4.06	2-Undecene	$C_{11}H_{22}$
7.	4.097	0.51	2-Methyldecalin	$C_{11}H_{20}$
8.	4.514	4.32	1-Dodecene	$C_{12}H_{24}$
9.	4.588	2.68	Dodecane	$C_{12}H_{26}$
10.	5.396	4.02	1-tridecene	$C_{13}H_{26}$
11.	5.474	2.46	Tridecane	$C_{13}H_{28}$
12.	5.594	0.62	3-Tridecene	$C_{13}H_{26}$
13.	6.269	9.12	1-Tetradecene	$C_{14}H_{28}$
14.	6.460	0.86	3-Tetradecene	$C_{14}H_{28}$
15.	6.782	0.59	Nonyl-cyclopentane	$C_{14}H_{28}$
16.	7.213	7.14	Pentadecane	$C_{15}H_{32}$
17.	7.305	0.63	5-Octadecene	$C_{18}H_{36}$
18.	7.370	0.82	1-methyl-4-(1-methylethenyl)-cyclohexane	$C_{10}H_{18}$
19.	7.639	2.25	Heptylcyclohexane	$C_{13}H_{26}$
20.	7.845	3.45	7-hexadecene	$C_{16}H_{32}$
21.	7.953	1.57	Hexadecane	$C_{16}H_{34}$
22.	8.079	0.81	Cyclohexadecane	$C_{16}H_{32}$
23.	8.614	4.64	8-Heptadecene	$C_{17}H_{34}$
24.	8.720	2.70	Heptadecane	$C_{17}H_{36}$
25.	8.843	1.60	3-Heptadecene	$C_{17}H_{34}$
26.	9.318	1.08	9-Octadecene	$C_{18}H_{36}$
27.	9.393	1.51	3-Octadecene	$C_{18}H_{36}$
28.	9.566	0.57	1-Octadecene	$C_{18}H_{36}$
29.	10.161	4.04	2-Heptadecanone	$C_{17}H_{34}O$
30.	10.700	11.31	Palmatic Acid	$C_{16}H_{42}O_2$
31.	11.332	2.85	1-Heneicosene	$C_{21}H_{42}$
32.	11.751	3.36	Oleic acid	$C_{18}H_{34}O_2$
33.	11.845	1.27	Petroselinic acid	$C_{18}H_{34}O_2$
34.	11.926	2.64	1-Docosene	$C_{22}H_{44}$
35.	12.495	2.44	1-Nonadecene	$C_{19}H_{38}$
36.	13.050	2.19	Cyclotetracosane	$C_{24}H_{48}$
37.	13.134	0.55	Tetracosane	$C_{24}H_{50}$
38.	13.590	1.49	12-Pentacosene	$C_{25}H_{50}$
39.	14.112	1.12	1-Hexacosene	$C_{26}H_{52}$
40.	14.617	1.15	10-Nonadecanone	$C_{19}H_{38}O$
41.	18.880	0.69	16-Hentriacontanone	$C_{31}H_{62}O$

4 Table 2: Compound of palm oil pyrolysis liquid fuel with zeolite H-X catalyst.

In the palm oil pyrolysis experiment using zeolite H-X catalyst, 41 compositions were identified with the help of the MS NIST17.LIB library system which were classified into three categories of more general chemical compounds, namely hydrocarbons, acids, and ketones as shown in Table 2. chemistry was useful for further simplifying the data and comparing the chemical comp4 ents in the produced liquid fuels with the commonly used liquid fuels. Figure 7 shows a diagram of the relative compounds

Journal of Physics: Conference Series

IOP Publishing

doi:10.1088/1742-6596/1751/1/012092

of the liquid fuel which explains that the main component of the liquid fuel was hydrocarbon at 77% which is the main component of the ideal fuel.

1751 (2021) 012092



Figure 7. Relative compounds of palm oil pyrolysis liquid using zeolite H-X.

4. Conclusion

Zeolite-X was synthesized with sodium silicate which was aged for 24 hours to produce zeolite with the best conditions as evider 23 by the XRD diffractogram pattern results that was similar with IZA standard. Zeolite-X was carried out by an ion-exchange process to produce zeolite H-X. The ion exchange process on the synthesized zeolite did not change the resulting XRD diffractogram pattern but did change the zeolite surface morphology observed from the SEM analysis results. Zeolite H-X was applied in pyrolysis experiments to produce liquid fuel. Liquid fuel has a component of 77% hydrocarbons, 16% acids, and 7% ketones.

5. References

- Mahari W A W, Chong C T, Cheng C K, Lee C L, Hendrata K, Yek P N Y and Lam S S 2018 Production of value-added liquid fuel via microwave co-pyrolysis of used frying oil and plastic waste *Energy* 162 309–317
- Shadangi K P and Mohanty K 2014 Thermal and catalytic pyrolysis of karanja seed to produce liquid fuel *Fuel* 115 434–442
- [3] Twaiq FA, Mohamed A R and Bhatia S 2003 Liquid hydrocarbon fuels from palm oil by catalytic cracking over aluminosilicate mesoporous catalyst with various Si/Al ratios *Microporous Mesoporous Mater.* 64(1-3) 95-107
- [4] Twaiq F A, Mohamed A R and Bhatia S 2004 Performance of composite catalyst in palm oil cracking for the production of liquid fuels and chemicals *FPT*. 85(11) 283-1300
- [5] Abnisa F, Daud W M A W, Ramalingam S, Azemi M N B M and Sahu J N 2013 Co-pyrolysis of palm shell and polystyrene waste mixtures to synthesis liquid fuel *Fuel* 108 311-318
- [6] Simanjuntak W, Sembiring S, Pandiangan K D, Pratiwi E and Syani F 2017 Hydrocarbon rich liquid fuel produced by co-pyrolysis of sugarcane bagasse and rubber seed oil using aluminosilicates derived from rice husk silica and alumunium metal as catalyst *Orient*. J. *Chem.* 33(6) 3218-3224
- [7] Nayan N K, Kumar S and Singh R K 2013 Production of the liquid fuel by thermal pyrolysis of neem seed *Fuel* 103 437–443
- [8] Alfernando O, Sarip R, Anggraini T, and Nazarudin 2019 Catalytic cracking of methyl ester from used cooking oil with Ni-ion-exchanged ZSM-5 catalyst *Makara J. Sci*.23(4) 169-178
- [9] Lu Q, Zhang Y, Tang Z, Li WZ and Zhu X F 2010 Catalytic upgrading of biomass fast pyrolysis vapors with titania and zirconia/titania based catalysts *Fuel* 89(8) 2096–2103
- [10] Vitolo S, Seggiani M, Frediani P, Ambrosini G and Politi L 1999 Catalytic upgrading of pyrolytic oils to fuel over different zeolites *Fuel* 78(10) 1147–59

ICASMI 2020		IOP Publishing
Journal of Physics: Conference Series	1751 (2021) 012092	doi:10.1088/1742-6596/1751/1/012092
[11] Stafanidis S.D. Kalogiannis K.G.	Iliopoulou E E Lappas	A A and Pilavachi P A 2011 In situ

- [11] Sterandris S D, Ralogiannis R G, inopoulou D F, Eappas A A and Fnavaeni F A 2011 in situ upgrading of biomass pyrolysis vapors: Catalyst screening on a fixed bed reactor *Bioresour Technol*. **102**(17) 8261–8267
- [12] Ying X, Tiejun W, Longlong M and Guanyi C 2012 Upgrading of fast pyrolysis liquid fuel from biomass over Ru/γ-Al₂O₃ catalyst *Energy Convers. Manag*. 55 172-177
- [13] Li Y, Li L and Yu, J 2017 Applications of zeolites in sustainable chemistry (Amsterdam North-Holland/American: Elsevier) 928-949
- [14] Qiang Z, Shen X, Guo M, Cheng F and Zhang M 2019 A simple hydrothermal synthesis of zeolite X from bauxite tailings for highly efficient adsorbing CO₂ at room temperature. *Microporous Mesoporous Mater.* 287 77-84
- [15] Ozdemir O D and Piskin S 2013 Zeolite X synthesis with different sources IJCEBS. 1(2) 229-232
- [16] Pandiangan K D, Arief S, Jamarun N and Simanjuntak W 2017 Synthesis of zeolite-X from rice husk silica and aluminum metal as a catalyst for transesterification of palm oil *JMES*. 8(5) 1797-1802
- [17] Babajide O, Musyoka N, Petrik L and Ameer F 2012 Novel zeolite Na-X synthesized from fly ash as a heterogeneous catalyst in biodiesel production *Catal. Today* 190(1) 54-60
- [18] Manadee S, Sophiphun O, Osakoo N, Supamathanon N, Kidkhunthod P, Chanlek N, Wittayakun J and Prayoonpokarach 2017 Identification of potassium phase in catalyst supported on zeolite NaX and performance in transesterification of jatropha seed oil *FPT*. **156** 62-67
- [19] Czuma N, Zarebska K, Motak M, Galvez M E and Costa P D 2020 Ni/Zeolite X derived from fly ash as catalyst for CO₂ methanation *Fuel* 267 1-7
- [20] Zarshenas K, Raisi A and Aroujalan A. 2016. Mixed matrix membrane of nano-zeolite NaX/poly (ether-block-amide) for gas separation applications J. Membr. Sci. 510 270–283
- [21] Brites-Nobrega F F, Lacerda I A, Santos S V, Amorim C C, Santana V S, Fernandes-Machado N R C, Ardisson J D, Henriques A B and Leao M M D 2014 Synthesis and characterization of new NaX zeolite-supported Nb, Zn, and Fe photocatalyst activated by visible radiation for appliation in wastewater treatment *Catal. Today* 240 168-175
- [22] Brea P, Delgado J A, Agueda V I, Gutierrez P and Uguina M A 2019 Multicomponet adsorption of H₂, CH₄, CO, and CO₂ in zeolites NaX, CaX, and MgX. Evaluation of performance in PSA cycles for hydrogen purification. *Microporous Mesoporous Mater.* 286 187-198
- [23] El-Nahas S, Osman A I, Arafat A S, Al-Muhtaseb A H and Salman H M 2020 Felice and affordable synthetic route of nano powder zeolite and its application in fast softening of water hardness J. Water Process. Eng. 33 1-18
- [24] Serati-Nouri H, Jafari A, Roshangar L, Dadashpour M, Pilehvar-Soltanahmadi Y and Zarghami N 2020 Biomedical applications of zeolite-based materials: A review. *Mater. Sci. Eng. C*. 116 1-13
- [25] Yan J, Li Y, Li H, Zhou Y, Xiao F, Li B and Ma X 2018 Effective removal of ruthenium (III) ions from wastewater by amidoxime modified zeolite X *Microchem. J.* 145 287-294
- [26] Yang L, Liu Z, Liu Z, Peng W, Liu Y and Liu C 2017 Correlation between H-ZSM-5 crystal size and catalytic performance in the methanol- to- aromatics reaction. *Chinese J. Catal.* 38(4) 683-690
- [27] Machado F N R C and Malachini Miotto D M 2005 Synthesis of Na–A and –X zeolites from oil shale ash *Fuel* 84(18) 2289–2294

Febriyanti_2021_J._Phys.__Conf._Ser._1751_012092

ORIGIN		
SIMIL	6% 11% 9% 6% arity index internet sources publications student p	APERS
PRIMA	RY SOURCES	
1	Submitted to Universitas Negeri Semarang Student Paper	3%
2	repository.lppm.unila.ac.id	2%
3	eprints.whiterose.ac.uk Internet Source	2%
4	Wasinton Simanjuntak, Kamisah Delilawati Pandiangan, Zipora Sembiring, Agustina Simanjuntak. "Liquid Fuel Production by Zeolite- A Catalyzed Pyrolysis of Mixed Cassava Solid Waste and Rubber Seed Oil", Oriental Journal of Chemistry, 2019 Publication	1%
5	Submitted to Universitas Muhammadiyah Surakarta Student Paper	1%
6	WWW.gssrr.org Internet Source	1%
7	scitepress.org	

1%

<1%

8 hdl.handle.net Internet Source

Jiashuai Yan, Ye Li, Haorui Li, Yuzhi Zhou, Huafeng Xiao, Bolin Li, Xiao Ma. "Effective removal of ruthenium (III) ions from wastewater by amidoxime modified zeolite X", Microchemical Journal, 2019 Publication

qian, Ting-Ting, De-Chang Li, and Hong Jiang. "Thermochemical Behavior of Tris(2-Butoxyethyl) Phosphate (TBEP) during Copyrolysis with Biomass", Environmental Science & Technology Publication

21 Zhiqin Qiang, Xianjiang Shen, Min Guo, Fangqin Cheng, Mei Zhang. "A simple hydrothermal synthesis of zeolite X from bauxite tailings for highly efficient adsorbing CO2 at room temperature", Microporous and Mesoporous Materials, 2019 Publication

12

www.bizvibe.com

<1%



Guanyi. "Upgrading of fast pyrolysis liquid fuel from biomass over Ru/γ-Al2O3 catalyst", Energy Conversion and Management, 2012

<1%

<1%

Publication

14 K D Pandiangan, W Simanjuntak, E Pratiwi, M Rilyanti. "Characteristics and catalytic activity of zeolite-a synthesized from rice husk silica and aluminium metal by sol-gel method", Journal of Physics: Conference Series, 2019 Publication

15 Takaaki Wajima, Yasuyuki Ikegami. "ZEOLITE SYNTHESIS FROM PAPER SLUDGE ASH VIA ACID LEACHING", Chemical Engineering Communications, 2007 Publication

- M Aimen Isa, Thiam Leng Chew, Yin Fong Yeong. "Zeolite NaY Synthesis by using Sodium Silicate and Colloidal Silica as Silica Source", IOP Conference Series: Materials Science and Engineering, 2018 Publication
- Wan Adibah Wan Mahari, Cheng Tung Chong, Chin Kui Cheng, Chern Leing Lee et al.
 "Production of value-added liquid fuel via microwave co-pyrolysis of used frying oil and plastic waste", Energy, 2018 Publication



<1%

<1% R Y Kurniawan, T Q Romadiansyah, A D 19 Tsamarah, N Widiastuti. "Synthesis of Zeolite-X from Bottom Ash for H Adsorption ", IOP Conference Series: Materials Science and Engineering, 2018 Publication



18

digilib.unila.ac.id **Internet Source**

Gourav Chatterjee, Krushna Prasad Shadangi, 21 Kaustubha Mohanty. "Effect of Catalyst Bed Height on the Yield and Composition of Nonedible Seed Pyrolytic Oil", Waste and Biomass Valorization, 2019 **Publication**

22

repository.uhamka.ac.id Internet Source

Ren, Lixia, Christopher G. Hardy, Shanfeng 23 Tang, Deon B. Doxie, Nasrollah Hamidi, and Chuanbing Tang. "Preparation of Side-Chain 18-e Cobaltocenium-Containing Acrylate Monomers and Polymers", Macromolecules, 2010. Publication

24

Yu-Ri Lee, June Thet Soe, Sigian Zhang, Ji-

<1% <1%

<1%

<**1**%

	Whan Ahn, Min Bum Park, Wha-Seung Ahn. "Synthesis of nanoporous materials via recycling coal fly ash and other solid wastes: A mini review", Chemical Engineering Journal, 2017 Publication	<1%
25	Soo-Young No. "Application of Liquid Biofuels to Internal Combustion Engines", Springer Science and Business Media LLC, 2019 Publication	<1%
26	A Simanjuntak, W Simanjuntak, K D. Pandiangan, Z Sembiring. "The Effect of Sugarcane Bagasse to Rubber Seed Oil Ratios on The Chemical Composition of Liquid Fuels Produced by Zeolite-y Catalyzed Pyrolysis", Journal of Physics: Conference Series, 2019 Publication	<1%
27	Wan Adibah Wan Mahari, Shin Ying Foong, Su Shiung Lam. "Chapter 12 Co-pyrolysis of Lignocellulosic Biomass and Polymeric Wastes for Liquid Oil Production", Springer Science and Business Media LLC, 2020 Publication	<1%

Exclude quotes	On	Exclude matches	Off
Exclude bibliography	On		