

PAPER • OPEN ACCESS

## Effect of natural zeolite and kaolin as a catalyst in the isothermal-catalytic cracking of real municipal solid waste (MSW) for bio-oil production

To cite this article: I M Gandidi *et al* 2018 *IOP Conf. Ser.: Earth Environ. Sci.* **160** 012018

View the [article online](#) for updates and enhancements.

### Related content

- [Co-cracking of real MSW into bio-oil over natural kaolin](#)  
I M Gandidi, M D Susila and N A Pambudi
- [Determination of Surface Energy of Natural Zeolite by Inverse Gas Chromatography](#)  
Ceyda Bilgiç and Naile Karakehya
- [Effects of natural zeolite and ferric oxide to electromagnetic and reflection loss properties of polyurethane nanocomposite](#)  
G Gultom, B Wirjosentono, M Ginting *et al.*

# Effect of natural zeolite and kaolin as a catalyst in the isothermal-catalytic cracking of real municipal solid waste (MSW) for bio-oil production

I M Gandidi<sup>1\*</sup>, M D Susila<sup>2</sup> and H Rustamaji<sup>3</sup>

<sup>1</sup> Department of Mechanical Engineering Education, Indonesia University of Education, Jl. Dr. Setiabudhi No. 229, Kota Bandung 40154, West Java, Indonesia

<sup>2</sup> Department of Mechanical Engineering, Faculty of Engineering, University of Lampung, Jl. S. Brojonegoro, Bandarlampung 35145, Indonesia

<sup>3</sup> Department of Chemical Engineering, Faculty of Engineering, University of Lampung, Jl. S. Brojonegoro, Bandarlampung 35145, Indonesia

\*Email: indra.gandidi@upi.edu

**Abstract.** A real MSW conversion into bio-oil by pyrolysis method had been investigated. The pyrolysis experiment was carried out in an isothermal fixed bed reactor at 400 °C for 60 min. Natural activated zeolite and kaolin catalysts were employed in this process with catalyst-MSW at ratio of 0.5 w/w. Influence of activated catalyst to pyrolysis productivity and bio-oil properties were studied. Comparison between zeolite and kaolin catalytic pyrolysis was examined and bio-oil products were analyzed by GC-MS. The yields of liquid fuel or bio-oil were found around 23.6 and 21.4% for kaolin and zeolite catalytic pyrolysis, respectively. The carbon range distribution in bio-oil were 65.38% of gasoline range (C<sub>5</sub>-C<sub>12</sub>) and 33.49% of diesel range (C<sub>13</sub>-C<sub>20</sub>) for activated kaolin catalytic cracking. Activated zeolite had 51.62% of gasoline range (C<sub>5</sub>-C<sub>12</sub>) and 48.37% of diesel range (C<sub>13</sub>-C<sub>20</sub>). The results showed that both of bio-oil products mostly contained paraffin and olefin. The use of kaolin as catalyst was better than zeolite in converting the real MSW into bio-oil.

## 1. Introduction

The open dumping system of municipal solid waste (MSW) in Indonesia has created a lot of impacts for people and environment in which the system is no longer relevant due to the limitations in the urban area [1]. The landfill becomes a habitat for insects, pests and bacteria that can spread various diseases in the open environment. The piles of garbage in the landfill will produce some leachate that contaminates the ground and surface water [2]. Furthermore, MSW will be degraded biochemically and produce methane gas into the atmosphere. It is known that the potential of methane gas pollution is about twenty times more dangerous than the pollution by CO<sub>2</sub> [3]. In addition, MSW is one of major contributors for flood and increased risk of global warming and greenhouse gas effect [4].

On the other hand, MSW is a material contains energy in the form of chemical bonds between molecules of carbon, hydrogen and oxygen. When the chemical bonds are destroyed, the organic material will release the chemical energy in the form of gas, liquid and solid which is commonly called biofuel [5,6]. The calorific value content is around 20.57 MJ/kg [7]. Thus, MSW is one of the potential energy materials that can be converted into bio-energy. Pyrolysis is one method proposed for bio-energy production from MSW. Pyrolysis is a thermal degradation in which MSW is converted into solid



fraction, liquid fraction consisting of paraffin, olefins, naphthene and aromatics, and gas at elevated temperature in the absence of oxygen [8]. Usually the temperature used is in the range of 400-600 °C. This process is intended to break down the long hydrocarbon chains into short-chain hydrocarbons. Hence, MSW appears to be eligible to be developed as a raw material for bio-oil production by pyrolysis technique [9-12]. MSW converted into bio-oil has attracted much attention due to its ease in storage, transport, and upgrading.

Recently, researches are focused on the catalysts to reduce the activation energy and to improve the thermal efficiency due to endothermic reaction at high temperature as well as the decomposition process improvement during catalytic cracking. The presence of catalyst will generate secondary cracking to the solids and liquids. Thus, resulted in higher pyrolytic products. Chika *et al* [13] carried out the catalytic pyrolysis by using Y-zeolite and ZSM-5 as catalyst to convert electric and electronic plastic waste into bio-oil, while Aida *et al* [14] used fluidized catalytic cracking (FCC) catalyst to convert plastic waste. Norbert *et al* [15] performed catalytic pyrolysis by Y-zeolite, FCC, MoO<sub>3</sub> and HZSM-5 to convert MSW and municipal plastic waste (MPW). Almeida and Marque [16] compared between thermal and HZSM-5-catalytic cracking to MPW. Funda *et al* [17] studied the catalyst efficiency of Y-zeolite,  $\beta$ -zeolite, equilibrium FCC, MoO<sub>3</sub>, Ni-Mo-catalyst, and HZSM-5 on the catalytic cracking of MSW and MPW. The studies mentioned above, used synthetic or commercial catalysts in the pyrolysis process which is high costs of production, faster deactivation time of catalyst by MSW impurities or contaminant, as well as unfavorable in the viewpoint of economic issues.

Nevertheless, available natural catalysts as zeolite, kaolin, and dolomite have been investigated as catalysts on pyrolysis process instead of commercial catalysts. Wenger [18] performed the experiment of catalytic pyrolysis to produce bio-oil from mixed plastic waste by using clay as the catalyst. Kyaw *et al* [19] carried out pyrolysis to compare between clay and dolomite as the catalyst. Panda *et al* [20] used kaolin in the polypropylene pyrolysis and Mochamad *et al* [21] carried out two stage pyrolysis of HDPE and polypropylene as raw material with natural zeolite as the catalyst to produce bio-oil. However, single component pyrolysis or MSW that was specified such as pure and mixed plastic material for bio-oil production was performed. However, the MSW characteristic in developing countries contains a huge variety of mixed waste and it is impossible to collect different kinds separately because of the large quantities. In addition, more information due to bio-oil characteristics from the real unseparated MSW pyrolysis is necessary prior to use as an engine fuel. Moreover, natural catalysts have different characteristics from each other and it is very dependent on the mining location and chemical composition of the natural catalyst. For instance, Si/Al ratios in the catalyst shows strong effects on the pyrolytic products. Significant effect on the decomposition process will be obtained under lower Si/Al ratio and increases the acidity of catalyst [22]. The selection of appropriate natural catalyst for real MSW pyrolysis is required. In addition, kaolin and zeolite are not used as catalyst in the pyrolysis process of real MSW.


This research was focused on the productivity and selectivity of natural zeolite and kaolin as a catalyst on pyrolysis process to produce bio-oil from the real MSW. The real MSW consists of biomass waste, various plastics waste, textile waste, papers waste, and rubber waste.

The characterization was carried on the composition and yield, chemical, and physical properties of bio-oil. Comparison between pyrolysis and conventional oils such as diesel-48 and gasoline-88 was performed to examine the possibility for conventional fuels substitution.

## 2. Material and Methods

### 2.1. Waste and catalyst for pyrolysis

The MSW was collected from the final disposal site located in Bakung District, Bandarlampung City. This MSW consisted of various wastes such as vegetable waste from the traditional market, garden waste, household waste, plastic waste, paper/cardboard, rubber waste, and textile waste. Samples were sun dried for 3-5 days. The dried MSW was then chopped into pieces smaller than 5-10 cm to provide proportional size with reactor capacity. The dry basis composition of MSW are shown in Figure 1.



**Figure 1.** The composition of MSW.

The natural zeolite and kaolin used in this study were obtained from the local source in Lampung Province, Indonesia and then ground by a hummer mill and sieved to 20-30 mesh. Zeolite and kaolin were activated thermally at 500 °C for 2 h to improve the active site and crystallinity. To examine the structure and surface of the natural zeolite and kaolin, the XRD was employed. The composition of the activated natural zeolite and kaolin is shown in Table 1. The high amount of SiO<sub>2</sub> and Al<sub>2</sub>O<sub>3</sub> in the natural zeolite and kaolin showed that zeolite and kaolin are proper to use as a catalyst. These compounds could increase the cracking efficiency and increase the pyrolytic products.

**Table 1.** X-Ray analysis for chemical composition of activated zeolite and kaolin.


Kind of catalyst	Compound	Concentration (%)
Zeolite	SiO <sub>2</sub>	68.5
	Al <sub>2</sub> O <sub>3</sub>	13.17
	Fe <sub>2</sub> O <sub>3</sub>	2.98
	MgO	1.15
	CaO	2.47
	K <sub>2</sub> O	1.80
	Na <sub>2</sub> O	1.06
	TiO <sub>2</sub>	0.14
Kaolin	SiO <sub>2</sub>	43.12
	Al <sub>2</sub> O <sub>3</sub>	46.07
	Fe <sub>2</sub> O <sub>3</sub>	0
	MgO	0.27
	CaO	0.3
	K <sub>2</sub> O	0.01
	ZnO	0.0064
	TiO <sub>2</sub>	0.74

Source: CV. Mina Tama, Bandarlampung

Figure 2 shows the X-ray patterns for both catalysts. The sharp peaks implied that natural zeolite and kaolin had good crystallinity and possibly gave strong effects in the decomposition of MSW and stable at high temperature.


## 2.2. Pyrolysis experiment and bio-oil analysis

The MSW sample was pyrolysed using a fixed bed vacuum reactor equipped with air lock valve between reactor and hopper to avoid the air took place of reactor entry. The reactor was made from stainless cylinder with 310 mm in height and 160 mm in internal diameter. The electrical heating jacket was connected to thermo-controller and thermocouple was taped around the reactor. The reactor was set vertically and connected to a nitrogen tank using rubber tube and then N<sub>2</sub> gas was introduced into the reactor for 3 min from the top, passed through and flowed out through the top of the reactor. The flow of nitrogen replaced the air from the reactor and permitted the pyrolysis reaction took place under inert vacuum condition.



**Figure 2.** X-Ray patterns of the activated zeolite and kaolin.

Nitrogen gas was introduced into the reactor and then the reactor was heated until reactor temperature reached to 400 °C with heating rate of 12°C. An amount of 750 g of mixed catalyst (250 g) –MSW (500 g) was put into reactor by the opened air lock valve. The reaction time was set for 60 min for both of pyrolysis experiments. The gas produced was flowed into vacuum gas cleaner as the first condenser to the shell and tube condensers at 20°C as the secondary condenser to separate the permanent gas and liquid. The gas was burned off to prevent emission from hydrocarbon gases. The char remained in the reactor was collected after the pyrolysis reaction was finished. The experimental apparatus is shown in Figure 3.



**Figure 3.** The experiment apparatus.

Regarding the pyrolytic products, products obtained from the pyrolysis could be divided into non-condensable gas fraction, solid fraction and liquid (bio-oil) fraction. From bio-oil yield that could be recovered, the hydrocarbon chains were in the gasoline range ( $C_5$ - $C_{12}$ ), diesel ( $C_{12}$ - $C_{20}$ ) and heavy oil ( $> C_{20}$ ) that consisted of paraffin, olefins, naphthenes and aromatics [23]. The pyrolysis liquid was analyzed using gas chromatography-mass spectrometry (GC-MS, QP2010S Shimadzu) which could be used to identify carbon number range and chemical composition. The column was DB-1 (Agilent J 100% dimethyl polysiloxane) capillary column, 30 m length with 0.25 mm diameter and 25  $\mu$ m film thickness. Helium was used as the gas carrier. The temperature was set in initial temperature of 60°C for 5 min followed by a heating rate of 5°C/min to 280 °C and held for 51 min. The estimation of the heating value of bio-oil was approached by carbon-hydrogen weight ratio [24]. Paraffin had the highest heating value followed by iso-paraffin, olefin, naphthenes and aromatic (PIONA). Also, the distributions of PIONA in each range of hydrocarbon were calculated to determine the selectivity behavior of natural zeolite and kaolin catalysts in the pyrolysis process.


### 3. Results and Discussion

#### 3.1. Physical properties of bio-oil

Table 2 shows the density and viscosity for conventional fuel and bio-oil. It shows that both of bio-oils from the natural catalytic cracking had similar density values and significantly different viscosity properties. The kinematic viscosity of natural kaolin was lower than the natural zeolite. It indicated that the natural kaolin had a good cracking reaction compared with the natural zeolite. However, both of bio-oils had properties close to diesel-48 and were acceptable to be considered as a future energy. Both of bio-oils had high solid and water contents due to impurities in the unwashed real MSW and direct catalytic as well. The solid content in the bio-oil was affected by ash from the biomass material.

**Table 2.** The physical properties of bio-oil.


Properties	Unit - Standard	Diesel	Gasoline	Kaolin	Zeolite
Cetane octane number		48 ( <i>cetane</i> )	88 ( <i>octane</i> )	-	-
Density@15°C	g/cm <sup>3</sup> ASTM D-1298	0.815-0.87	0.7-0.78	0.8038	0.8076
Kinematic viscosity@40°C	cSt ASTM D-445	2.0-5.0	0.4-0.8	2.0345	2.4775
Flash point	°C ASTM D-93	min 60	min 40	min 5	min 5
Pour point	°C	max 18	-	-	-
Water content	% Vol ASTM D-1744	max 0.05	-	3	2.5
Oil content	% Vol ASTM D-1744	-	-	86	90
Solid content	% Vol ASTM D-482	-	-	11	7.5

**Figure 4.** Mass yield of pyrolytic products.

### 3.2. Yield and chemical properties of bio-oil


The products from the MSW pyrolysis are shown in Figure 4. Catalytic cracking produced from natural kaolin and zeolite by pyrolysis is 23.6 and 21.4%, respectively. Kaolin shows higher yield compared to zeolite. This indicated that natural kaolin had a better productivity than the natural due its higher active site and higher acidity. However, the highest yield on the gaseous product and appearance of water content in the bio-oil implied that further drying for MSW was required and temperature of condensation environment around 20°C was unfavorable. Moreover, the low bio-oil yield could also be associated with the short reaction time and the long residence time of the gas in the reactor [25]. A similar result was presented by Panda and Singh [26] that used kaolin as a catalyst in plastic waste pyrolysis.

Figure 5 shows the carbon distribution range in the conventional and pyrolytic oils. The pyrolytic oil from mostly contains gasoline (C<sub>5</sub>-C<sub>12</sub>) followed by diesel (C<sub>13</sub>-C<sub>20</sub>) and a small amount of heavy oil (>C<sub>20</sub>).



**Figure 5.** Carbon distribution range on conventional and pyrolysis fuel.

Bio-oil by natural kaolin catalytic consisted of 65.38% gasoline fraction and 33.49% of diesel fraction. Meanwhile bio-oil by natural zeolite showed 51.62% of gasoline fraction and 48.37% of diesel fraction. Clearly, natural kaolin had shown better properties as a catalyst for the production of bio-oil from MSW compared with natural zeolite, although natural zeolite did not have heavy oil fraction in the bio-oil.




**Figure 6.** A comparison of mass species between bio-oil and conventional fuel.

Figure 6 reveals the organic components in the bio-oil in which most of organic components in the bio-oil were paraffin and olefin with small amount of aromatic, alcohol and acid. Only slight difference in the amount of paraffin and olefin between natural kaolin and natural zeolite in catalytic cracking process. Consequently, bio-oils from natural kaolin and natural zeolite catalytic pyrolysis showed the same caloric values. It illustrated that both of natural catalysts at 400 °C and 60 min had similarities in the selectivity behavior.

Figure 7 shows the PIONA contents in each hydrocarbon range on the pyrolytic bio-oil, reveals that gasoline fraction contained more olefin than paraffin, otherwise with the diesel fraction for both of pyrolytic bio-oils. This composition was significantly affected by the plastic and biomass in MSW which determined the chemical reaction during the process of pyrolysis. The presence of impurities and natural catalyst in the MSW was also allegedly plays an important role to the bio-oil composition [27].





**Figure 7.** Number of mass species in each hydrocarbon range.

#### 4. Conclusion

Real MSW is a great potential raw material to be converted into paraffin and olefin by thermal-catalytic cracking. Activated kaolin and zeolite can increase the productivity of bio-oil quite low in its selectivity. Kaolin demonstrated a better capability for pyrolysis process than zeolite. The upgrading process to enhance the pyrolysis oil yield is necessary to obtain bio-oil with gasoline range.

#### References

- [1] Arinal H, Gandidi I M and Harmen 2010 *Final Report of Strategic Research Grant: Integrated Waste Management System of Bandarlampung City as an Effort of Environmental Conservation and Bioenergy Production* (Bandarlampung, Indonesia: Lampung University)
- [2] Le Courtouis A and World Bank 2012 *Municipal Solid Waste: Turning a Problem into Resource* <http://www.ccacoalition.org/en/resources/municipal-solid-waste-turning-problem-resource>
- [3] Haradhan M 2012 **2** 3–10
- [4] Hari B D and Sameer A 2013 *Habitat Int.* **38** 100–5.
- [5] Ebru A and Ahmet D 2009 *5<sup>th</sup> Int. Advanced Technology Symp.*, Karabuk, Turkey
- [6] McKendry P 2002 *Bioresource Technol.* **83** 37–46.
- [7] Ari D P, Kilbergen W, Gultom and Aryadi S 2007 *Final Report of Feasibility Study: MSW-Electricity Power Plant in Bandung City* (Bandung, Indonesia: Bandung Institute of Technology)
- [8] Hossain A K and Davies P A 2010 *Renew. Sust. Energy Rev.* **21** 165–89
- [9] Liu Y Q, Wang J, Dong J and Thay J H 2012 *3<sup>rd</sup> Int. Conf. Industrial and Hazardous Waste Management* Singapore
- [10] Seung S K, Jinsoo K, Jong K J, Young K P and Chan J P 2013 *Renewable Energy* **54** 241–7
- [11] Velghe I, Carleer R, Yperman J and Schreurs S 2011 *J. Anal. App. Pyrolysis.* **92** 366–75
- [12] Ayhan D 2004 *J. Anal. App. Pyrolysis* **72** 97–102
- [13] Chika M, Jude A O and Paul T W 2015 *Catalytic Pyrolysis of Waste Plastic from Electrical and Electronic Equipment* (Leeds, United Kingdom: Energy Research Institute, Faculty of Engineering, University of Leeds)
- [14] Aida Isma M I, Salmiaton A and Nur Dinie K B 2015 *Int. J. Env. Sci. Dev.* **6** 606–9
- [15] Norbert M, Ates F and Borsodi N 2013 *Bioresource Technol.* **144** 370–9
- [16] Almeida D and Marques M D F 2015 *Polimeros* **26** 44–51

- [17] Funda A, Miskolczi N and Borsodi N 2013 *Bioresource Technol.* **133** 443–54
- [18] Wenger J 2015 *J. Materials Science and Engineering* **5** 183–5
- [19] Kyaw K T and Hmwe C S S 2015 *Int. J. Advances in Engineering & Technol.* **8 (5)** 794–802
- [20] Panda A K and Singh R K 2013 *Advances in Energy Engineering* **1** 74–84
- [21] Mochamad S, Harwin S, Tinton N, Putri N, Shou C, Zainal A and Kunio Y 2014 *Energy Procedia* **47** 180–8
- [22] Wang J L and Wang L L 2011 *Energy Sources.* **33** 1940–8
- [23] Aguado J, Serrano D P, Guillermo S M and Madrid S 2007 *J. Anal. App. Pyrolysis* **79** 415–23
- [24] Riazi M R 2005 *Characterization and Properties of Petroleum Fractions* (Philadelphia: ASTM International) pp 30–84
- [25] Ayhan D 2009 *Energy Sources* **31** 1186–93
- [26] Panda A K and Singh R K 2014 *Int. J. Environment and Waste Management* **13** 104–14
- [27] Borsodi N, Miskolczi N, Angyal A, Bartha L, Kohan J and Lengyel A 2011 *45<sup>th</sup> International Petroleum Conference*, Bratislava, Slovak Republic